



Designation: B625 – 21



www.dlsspipeline.com

info@dlsspipe.com

Standard Specification for Ni-Fe-Cr-Mo-Cu-N Low-Carbon Alloy, Ni-Fe-Cr-Si Alloy, Cr-Ni-Fe-N Low-Carbon Alloy, Fe-Ni-Cr-Mo-Cu-N Alloy, and Ni-Fe-Cr-Mo-N Alloy Plate, Sheet, and Strip¹

This standard is issued under the fixed designation B625; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers nickel-iron-chromium-molybdenum-copper-nitrogen low-carbon alloy, nickel-iron-chromium-silicon alloy, chromium-nickel-iron-nitrogen low-carbon alloy, iron-nickel-chromium-molybdenum-copper-nitrogen alloy, and nickel-iron-chromium-molybdenum-nitrogen alloy plate, sheet, and strip in the annealed temper.

1.2 ASTM International has adopted definitions whereby some grades, such as UNS N08904, previously in this specification were recognized as stainless steels, because those grades have iron as the largest element by mass percent. Such grades are under the oversight of ASTM Committee A01 and its subcommittees. The products of N08904 previously covered in this specification are now covered by Specifications [A240/A240M](#) and [A480/A480M](#).

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Nov. 1, 2021. Published November 2021. Originally approved in 1977. Last previous edition approved in 2017 as B625 – 17. DOI: 10.1520/B0625-21.

2. Referenced Documents

2.1 ASTM Standards:²

[A240/A240M](#) Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

[A480/A480M](#) Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip

[B906](#) Specification for General Requirements for Flat-Rolled Nickel and Nickel Alloys Plate, Sheet, and Strip

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *plate, n*—material $\frac{3}{16}$ in. (4.76 mm) and over in thickness and over 10 in. (254 mm) in width.

3.1.2 *sheet, n*—material under $\frac{3}{16}$ in. (4.76 mm) in thickness and 24 in. (609.6 mm) and over in width. Material under $\frac{3}{16}$ in. (4.75 mm) in thickness and in all widths with No. 4 finish.

3.1.3 *strip, n*—material under $\frac{3}{16}$ in. (4.76 mm) in thickness and under 24 in. (609.6 mm) in width.

4. General Requirements

4.1 Material furnished in accordance with this specification shall conform to the applicable requirements of the current edition of Specification [B906](#) unless otherwise provided herein.

5. Ordering Information

5.1 Orders for material under this specification shall include the following information:

5.1.1 Quantity (weight or number of pieces),

5.1.2 Alloy name or UNS number,

5.1.3 Form—Plate, sheet, or strip,

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements^A

Elements	UNS N08925	UNS N08932	UNS N08354	UNS N08034	UNS N08031	UNS N08926	UNS N08830	UNS N08935	UNS R20033
Carbon	0.020	0.020	0.030	0.01	0.015	0.020	0.015	0.030	0.015
Manganese	1.00	2.00	1.00	1.0–4.0	2.0	2.00	3.0–6.0	1.2	2.0
Phosphorus	0.045	0.025	0.030	0.020	0.020	0.03	0.035	0.030	0.02
Sulfur	0.030	0.010	0.010	0.010	0.010	0.01	0.010	0.020	0.01
Silicon	0.50	0.40	1.00	0.1	0.3	0.5	1.00	0.5	0.50
Nickel	24.00–26.00	24.0–26.0	34.0–36.0	33.5–35.0	30.0–32.0	24.00–26.00	29.0–34.0	34.0–36.0	30.0–33.0
Chromium	19.00–21.00	24.0–26.0	22.0–24.0	26.0–27.0	26.0–28.0	19.00–21.00	20.0–24.0	26.0–28.0	31.0–35.0
Molybdenum	6.0–7.0	4.5–6.5	7.0–8.0	6.0–7.0	6.0–7.0	6.0–7.0	4.5–6.5	6.1–7.1	0.50–2.0
Copper	0.8–1.5	1.0–2.0	...	0.5–1.5	1.0–1.4	0.5–1.5	0.50–2.00	0.4	0.30–1.20
Cobalt	...	...	...	...	...	...	0.50–3.5	...	...
Tungsten	...	...	...	...	...	...	0.20–1.80	...	...
Nitrogen	0.10–0.20	0.15–0.25	0.17–0.24	0.10–0.25	0.15–0.25	0.15–0.25	0.20–0.55	0.25–0.36	0.35–0.60
Iron	balance	balance	balance	balance	balance	balance	balance	balance	balance
Aluminum	...	...	...	0.3	...	...	...	...	...

^A Maximum %, unless range or minimum is indicated.

TABLE 2 Mechanical Property Requirements

Alloy	Form	Tensile Strength, min, ksi (MPa)	Yield Strength (0.2 % offset), min, psi (MPa)	Elongation in 2 in. or 50.8 mm, or 4D, min, %
UNS N08925	sheet	87 (600)	43 000 (295)	40
	strip	87 (600)	43 000 (295)	40
	plate	87 (600)	43 000 (295)	40
UNS N08932 UNS N08031	plate	87 (600)	44 000 (305)	40
	sheet	94 (650)	40 000 (276)	40
	strip	94 (650)	40 000 (276)	40
UNS N08034	plate	94 (650)	40 000 (276)	40
	sheet	94 (650)	40 000 (280)	40
	strip	94 (650)	40 000 (280)	40
UNS N08926	plate	94 (650)	40 000 (280)	40
	sheet	94 (650)	43 000 (295)	35
	strip	94 (650)	43 000 (295)	35
UNS N08354	plate	94 (650)	43 000 (295)	35
	sheet	93 (640)	43 000 (295)	40
	strip	93 (640)	43 000 (295)	40
UNS N08830	plate	93 (640)	43 000 (295)	40
	sheet	110 (760)	55 000 (380)	40
	strip	110 (760)	55 000 (380)	40
UNS N08935	plate	110 (760)	55 000 (380)	40
	sheet	109 (750)	62 000 (425)	40
	strip	109 (750)	62 000 (425)	40
UNS R20033	plate < 0.25 in. (6.35 mm)	109 (750)	62 000 (425)	40
	plate ≥ 0.25 in. (6.35 mm)	102 (700)	51 000 (350)	40
	sheet	109 (750)	55 000 (380)	40
	strip	109 (750)	55 000 (380)	40
	plate	109 (750)	55 000 (380)	40

5.1.4 Dimensions,

5.1.5 Type edge required, for strip only (see Specification B906),

5.1.6 Finish (see Specification B906)—For sheet with No. 4 finish, specify whether one or both sides are to be polished,

5.1.7 ASTM designation,

5.1.8 Additions to the specification or special requirements,

5.1.9 Certification or test reports—State if certification or test reports are required, and

5.1.10 Source inspection—State if inspection is required.

6. Chemical Composition

6.1 The material shall conform to the composition limits specified in Table 1. One test per lot is required as defined in Specification B906.

6.2 If a product analysis is made by the purchaser, the material shall conform to the product (check) analysis variations in Specification B906.

7. Mechanical Properties and Other Requirements

7.1 *Tensile and Hardness Requirements*—The material shall conform to the mechanical property requirements specified in Table 2. One test per lot is required as defined in Specification B906.

8. Dimensions and Permissible Variations

8.1 *Sheet*—The material shall be furnished in accordance with the dimensional requirements established in Specification B906.

9. Keywords

9.1 plate; sheet; strip; UNS N08031; UNS N08034; UNS N08354; UNS N08830; UNS N08925; UNS N08926; UNS N08932; UNS N08935; UNS R20033

SUMMARY OF CHANGES

Committee B02 has identified the location of selected changes to this standard since the last issue (B625 – 17) that may impact the use of this standard. (Approved Nov. 1, 2021.)

- | | |
|---|---|
| (1) Changed the title to delete UNS numbers and include new alloy UNS N08935 (Ni-Fe-Cr-Mo-N Alloy). | (3) Added chemistry data for UNS N08935 to Table 1. |
| (2) Added new alloy UNS N08935 (nickel-iron-chromium-molybdenum-nitrogen alloy) to scope. | (4) Added mechanical property data to Table 2 for UNS N08935. |
| | (5) Added UNS N08935 to Keywords. |

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>