



Standard Specification for UNS N08028 Seamless Pipe and Tube¹

This standard is issued under the fixed designation B 668; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers UNS N08028 seamless cold-finished or hot finished pipe and tube intended for general corrosive service. The general requirements are covered in Specification B 829.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer; to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

B 829 Specification for General Requirements for Nickel and Nickel Alloys Seamless Pipe and Tube

3. General Requirement

3.1 Material furnished under this specification shall conform to the applicable requirements of Specification B 829 unless otherwise provided herein.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

- 4.1.1 Alloy name or UNS number,
- 4.1.2 ASTM designation and year of issue,
- 4.1.3 *Dimensions:*
 - 4.1.3.1 Outside diameter, minimum or average wall thickness (in inches or millimetres, not gage number), and length,
 - 4.1.3.2 Standard pipe size, schedule and length,
- 4.1.4 Quantity (feet or metres, or number of pieces),
- 4.1.5 Optional requirements,
- 4.1.6 *Certification*—State if certification is required,
- 4.1.7 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished, and
- 4.1.8 *Purchaser Inspection*—If the purchaser wishes to witness tests or inspection of material at the place of manufacture, the purchase order must so state, indicating which tests or inspections are to be witnessed.

5. Materials and Manufacture

5.1 Pipe and tube shall be furnished in the solution-annealed condition.

NOTE 1—The recommended heat treatment shall consist of heating the material to a temperature of 1975 to 2100°F (1080 to 1150°C) with subsequent quenching in water or rapidly cooling by other means.

5.2 The scale shall be removed by suitable means. When bright annealed, scale removal operations are not necessary.

6. Chemical Composition

6.1 The material shall conform to the requirement prescribed in Table 1.

TABLE 1 Chemical Requirements

Element	Composition, %
Carbon, max	0.030
Silicon, max	1.0
Manganese, max	2.50
Phosphorus, max	0.030
Sulfur, max	0.030
Chromium	26.0–28.0
Nickel	30.0–34.0
Molybdenum	3.0–4.0
Copper	0.6–1.4
Iron	remainder ^A

^A Determined arithmetically by difference.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Nov. 1, 2005. Published November 2005. Originally approved in 1980. Last previous edition approved in 2000 as B 668 – 00.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

6.1.1 A chemical analysis shall be made on each lot of material as described in Specification **B 829**.

6.2 If a product (check) analysis is performed by the purchaser, the material shall conform to **Table 1** subject to the product (check) analysis variations prescribed in Specification **B 829**.

7. Mechanical Properties and Other Requirements

7.1 The material shall conform to the mechanical properties prescribed in **Table 2**. One test is required for each lot, as defined in Specification **B 829**.

TABLE 2 Tensile Requirements

Tensile Strength, min, ksi (MPa)	Yield Strength, 0.2 % Offset, min, ksi (MPa)	Elongation in 2 in. (50.8 mm) or 4D, min, %
73 (500)	31 (214)	40

7.1.1 One tension test shall be made on each lot of pipe or tube.

7.2 *Flaring Test*—One flaring test shall be made on a specimen from one end of one pipe or tube from each lot of finished tubes.

7.3 *Hydrostatic Test or Nondestructive Test*:

7.3.1 Each pipe or tube shall be subjected to either the hydrostatic test or the nondestructive electric test at the manufacturer's option. The purchaser may specify which test is to be used.

8. Dimensions and Permissible Variations

8.1 *Outside Diameter and Wall Thickness*—The permissible variations in the outside diameter and the wall thickness shall not exceed those prescribed in Tables 3, 4 and 5 of Specification **B 829**.

9. Keywords

9.1 seamless tube; UNS N08028

SUMMARY OF CHANGES

Committee B02 has identified the location of selected changes to this standard since the last issue (B 668 – 00) that may impact the use of this standard.

(1) Addition of **1.3**.

(2) Revision of **4.1**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).