



Designation: B906 – 22



www.dlsspipeline.com

info@dlsspipe.com

Standard Specification for General Requirements for Flat-Rolled Nickel and Nickel Alloys Plate, Sheet, and Strip¹

This standard is issued under the fixed designation B906; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers a group of general requirements that, unless otherwise specified in the purchase order or in an individual specification, shall apply to rolled nickel and nickel alloy plate, sheet, and strip, under each of the following specifications issued by ASTM: Specifications [B127](#), [B162](#), [B168](#), [B333](#), [B409](#), [B424](#), [B434](#), [B435](#), [B443](#), [B463](#), [B536](#), [B575](#), [B582](#), [B599](#), [B620](#), [B625](#), [B670](#), [B688](#), [B709](#), [B718](#), [B755](#), [B814](#), [B818](#), [B872](#).

1.2 In case of any conflicting requirements, the requirements of the purchase order, the individual material specification, and this general specification shall prevail in the sequence named.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels](#)

[A693 Specification for Precipitation-Hardening Stainless and Heat-Resisting Steel Plate, Sheet, and Strip](#)

[B127 Specification for Nickel-Copper Alloy Plate, Sheet, and Strip](#)

[B162 Specification for Nickel Plate, Sheet, and Strip](#)

[B168 Specification for Nickel-Chromium-Aluminum Alloys \(UNS N06699\), Nickel-Chromium-Iron Alloys \(UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06696\), Nickel-Chromium-Cobalt-Molybdenum Alloy \(UNS N06617\), Nickel-Iron-Chromium-Tungsten Alloy \(UNS N06674\), and Nickel-Chromium-Molybdenum-Copper Alloy \(UNS N06235\) Plate, Sheet, and Strip](#)

[B333 Specification for Nickel-Molybdenum Alloy Plate, Sheet, and Strip](#)

[B409 Specification for Nickel-Iron-Chromium Alloy Plate, Sheet, and Strip](#)

[B424 Specification for Nickel-Iron-Chromium-Molybdenum-Copper Alloys Plate, Sheet, and Strip](#)

[B434 Specification for Nickel-Molybdenum-Chromium-Iron Alloys \(UNS N10003, UNS N10242\) Plate, Sheet, and Strip](#)

[B435 Specification for UNS N06002, UNS N06230, UNS N12160, and UNS R30556 Plate, Sheet, and Strip](#)

[B443 Specification for Nickel-Chromium-Molybdenum-Columbium Alloy and Nickel-Chromium-Molybdenum-Silicon Alloy Plate, Sheet, and Strip](#)

[B463 Specification for UNS N08020 Alloy Plate, Sheet, and Strip](#)

¹ This specification is under the jurisdiction of ASTM Committee [B02](#) on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee [B02.07](#) on Refined Nickel and Cobalt and Their Alloys.

Current edition approved July 15, 2022. Published August 2022. Originally approved in 2000. Last previous edition approved in 2019 as B906 – 19. DOI: 10.1520/B0906-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

B536 Specification for Nickel-Iron-Chromium-Silicon Alloys Plate, Sheet, and Strip

B575 Specification for Low-Carbon Nickel-Chromium-Molybdenum, Low-Carbon Nickel-Chromium-Molybdenum-Copper, Low-Carbon Nickel-Chromium-Molybdenum-Tantalum, Low-Carbon Nickel-Chromium-Molybdenum-Tungsten, and Low-Carbon Nickel-Molybdenum-Chromium Alloy Plate, Sheet, and Strip

B582 Specification for Nickel-Chromium-Iron-Molybdenum-Copper Alloy Plate, Sheet, and Strip

B599 Specification for Nickel-Iron-Chromium-Molybdenum-Niobium Stabilized Alloy Plate, Sheet, and Strip

B620 Specification for Nickel-Iron-Chromium-Molybdenum Alloy (UNS N08320) Plate, Sheet, and Strip

B625 Specification for Ni-Fe-Cr-Mo-Cu-N Low-Carbon Alloy, Ni-Fe-Cr-Si Alloy, Cr-Ni-Fe-N Low-Carbon Alloy, Fe-Ni-Cr-Mo-Cu-N Alloy, and Ni-Fe-Cr-Mo-N Alloy Plate, Sheet, and Strip

B670 Specification for Precipitation-Hardening Nickel Alloy (UNS N07718) Plate, Sheet, and Strip for High-Temperature Service

B688 Specification for Chromium-Nickel-Molybdenum-Iron (UNS N08367) Plate, Sheet, and Strip

B709 Specification for Iron-Nickel-Chromium-Molybdenum Alloy (UNS N08028) Plate, Sheet, and Strip

B718 Specification for Nickel-Chromium-Molybdenum-Cobalt-Tungsten-Iron-Silicon Alloy Plate

B755 Specification for Nickel-Chromium-Molybdenum-Tungsten Alloys (UNS N06110) Plate, Sheet, and Strip (Withdrawn 2021)³

B814 Specification for Nickel-Chromium-Iron-Molybdenum-Tungsten Alloy (UNS N06920) Plate, Sheet, and Strip

B818 Specification for Cobalt-Chromium-Nickel-Molybdenum-Tungsten Alloy (UNS R31233) Plate, Sheet and Strip

B872 Specification for Precipitation-Hardening Nickel Alloys Plate, Sheet, and Strip

B880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

B899 Terminology Relating to Non-ferrous Metals and Alloys

E8/E8M Test Methods for Tension Testing of Metallic Materials

E10 Test Method for Brinell Hardness of Metallic Materials

E18 Test Methods for Rockwell Hardness of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E39 Methods for Chemical Analysis of Nickel (Withdrawn 1995)³

E55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition

E76 Test Methods for Chemical Analysis of Nickel-Copper Alloys (Withdrawn 2003)³

E112 Test Methods for Determining Average Grain Size

E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

E1473 Test Methods for Chemical Analysis of Nickel, Cobalt and High-Temperature Alloys

2.2 *AIAG Standard:*

B-5 Primary Metals Identification Tag Application Standard⁴

2.3 *ANSI Standard:*

Accredited Standards Committee X 12 (ANSI ASC X 12)⁵

2.4 *ASME Standard:*

ASME Boiler and Pressure Vessel Code Section IX⁶

3. Terminology

3.1 *Definitions of Terms:*

3.1.1 The terms and definitions of Terminology **B899** are applicable to this specification.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *plate, n*—material $\frac{3}{16}$ in. (4.76 mm) and over in thickness and over 10 in. (250 mm) in width. Finishes for plate are actually shown in Section **13**.

3.2.2 *sheet, n*—material under $\frac{3}{16}$ in. (4.76 mm) in thickness and 24 in. (600 mm) and over in width. Finishes for sheet are actually shown in Section **11**.

3.2.3 *strip, n*—cold-rolled material under $\frac{3}{16}$ in. (4.76 mm) in thickness and under 24 in. (600 mm) in width. Finishes are detailed in Section **12** for strip, and strip edges in Section **14** for Cold-Rolled Strip.

3.2.4 *cold work, n*—the changing of mechanical properties by work hardening.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to, the following:

4.1.1 Quantity (weight and number of pieces),

4.1.2 Name of material,

4.1.3 Condition (hot-rolled, cold-rolled, annealed, heat-treated),

4.1.4 Finish (see Section **11** for Sheet, Section **12** for Strip, and Section **13** for Plates). In the case of polished finishes, specify whether one or both sides are to be polished,

4.1.5 Form (plate, sheet, or strip),

4.1.6 Dimensions (thickness, width, length),

⁴ Available from Automotive Industry Action Group (AIAG), 26200 Lahser Rd., Suite 200, Southfield, MI 48034, <http://www.aiag.org>.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁶ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

³ The last approved version of this historical standard is referenced on www.astm.org.

4.1.6.1 Thickness shall be ordered to decimal or fractional thickness. The use of the gauge number is discouraged as being an archaic term of limited usefulness not having general agreement on meaning. The gauge number shall not be a basis for rejection.

4.1.6.2 Thickness, width, and length, when applicable, should be ordered in the same units, for example, 0.060 in. by 48 in. by 120 in. (1.52 mm by 1219 mm by 3048 mm),

4.1.7 Edge, strip only (see Section 14 for Cold-Rolled Strip),

4.1.8 Type, refer to the applicable material specification,

4.1.9 Specification designation and date of issue,

4.1.10 Additions to specification or special requirements,

4.1.11 Restrictions (if desired) on methods for determining yield strength (see appropriate footnote to mechanical properties table of the basic material specification),

4.1.12 Restrictions on weld repair (see Section 17),

4.1.13 Marking requirements (see Section 22),

4.1.14 Preparation for delivery (see Section 22), and over.

5. Process

5.1 The material shall be manufactured/produced by the following or as specified in the applicable material specification.

5.1.1 The material shall be made by one of the following processes: electric-arc, electric-induction, or other suitable processes.

5.1.2 If a specific type of melting is required by the purchaser, it shall be so specified on the purchase order.

5.1.3 If a specific type of remelt is required by the purchaser, it shall be so specified on the purchase order.

6. Chemical Composition

6.1 In case of disagreement, the chemical composition shall be determined in accordance with the following methods:

UNS No. Prefixes	ASTM Method
N02	E39
N04	E76
N06, N08	E1473

6.2 The ladle analysis of the material shall conform to the chemical requirements prescribed by the individual product specification.

6.3 The product (check) analysis of the material shall meet the requirements of Specification B880.

7. Sampling

7.1 *Lots for Chemical Analysis and Mechanical Testing:*

7.1.1 A lot for chemical analysis shall consist of one heat.

7.1.2 A lot of plate, sheet, or strip for mechanical testing shall be defined as the material from one heat in the same condition and specified thickness.

7.2 *Sampling for Chemical Analysis:*

7.2.1 A representative sample shall be obtained from each heat during pouring or subsequent processing.

7.2.2 Product (check) analysis shall be wholly the responsibility of the purchaser.

7.3 *Sampling for Mechanical Testing*—Representative samples shall be taken from each lot of finished material.

8. Number of Tests and Retests

8.1 *Chemical Analysis*—One test per heat.

8.2 *Tension Tests*—One test per lot.

8.3 *Grain Size*—One test per lot.

8.4 *Retests*—If one of the specimens used in the above tests of any lot fails to meet the specified requirements, two additional specimens shall be taken from different sample pieces and tested. The results of the tests on both of these specimens shall meet the specified requirements.

9. Specimen Preparation

9.1 Tension test specimens shall be taken from material in the final condition and tested transverse to the direction of rolling when width will permit.

9.2 Tension test specimens shall be any of the standard or subsize specimens shown in Test Methods E8/E8M.

9.3 In the event of disagreement, referee specimens shall be as follows:

9.3.1 Full thickness of the material, machined to the form and dimensions shown for the sheet-type specimen in Test Methods E8/E8M for material under ½ in. (12.7 mm) in thickness.

9.3.2 The largest possible round specimen shown in Test Methods E8/E8M for material ½ in. (12.7 mm) and over.

10. Test Methods

10.1 The chemical composition and mechanical properties of the material as enumerated in this specification shall be determined, in case of disagreement, in accordance with the following ASTM standards:

10.1.1 *Chemical Analysis*—Test Methods E1473. For elements not covered by Test Methods E1473, the referee test method shall be as agreed upon between the manufacturer and the purchaser. The nickel composition shall be determined arithmetically by difference.

10.1.2 *Tension Test*—Test Methods E8/E8M.

10.1.3 *Rockwell Hardness Test*—Test Methods E18.

10.1.4 *Hardness Conversion*—Hardness Conversion Tables E140.

10.1.5 *Grain Size*—Test Methods E112.

10.1.6 *Determining Significant Places*—Practice E29.

10.1.7 *Method of Sampling*—Practice E55.

10.2 For purposes of determining compliance with the limits in this specification, an observed or calculated value shall be rounded in accordance with the rounding method of Practice E29:

Test Requirement	Rounded Unit for Observed or Calculated Value
Chemical composition and tolerances	nearest unit in the last righthand place of figures of the specified limit
Tensile strength and yield strength	nearest 1000 psi (7 Mpa)
Elongation	nearest 1 %

11. Finish for Sheet

11.1 The type of finish available on sheet products are:

11.1.1 No. 1 Finish—Hot-rolled, annealed, and descaled.

11.1.2 No. 2D Finish—Cold-rolled, dull finish.

11.1.3 No. 2B Finish—Cold-rolled, bright finish.

11.1.3.1 *Bright Annealed Finish*—A bright cold-rolled finish retained by final annealing in a controlled atmosphere furnace.

11.1.4 No. 3 Finish—Intermediate Polished finish, one or both sides.

11.1.5 No. 4 Finish—General purpose polished finish, one or both sides.

11.1.6 No. 6 Finish—Dull satin finish, Tampico brushed, one or both sides.

11.1.7 No. 7 Finish—High luster finish.

11.1.8 No. 8 Finish—Mirror finish.

11.1.9 Sheets can be produced with one or two sides polished. When polished on one side only, the other side may be rough ground in order to obtain necessary flatness.

NOTE 1—Explanation of Sheet Finishes:

No. 1—This finish is produced by hot rolling to specified thickness followed by annealing and descaling. It is generally used in industrial applications, such as for heat and corrosion resistance, where smoothness of finish is not of particular importance.

No. 2D—Produced on either hand sheet mills or continuous mills by cold rolling to the specified thickness, annealing and descaling. The dull finish may result from the descaling or pickling operation or may be developed by a final light cold-rolled pass on dull rolls. The dull finish is favorable for retention of lubricants on the surface in deep drawing operations. This finish is generally used in forming deep-drawn articles which may be polished after fabrication.

No. 2B—Commonly produced the same as 2D, except that the annealed and descaled sheet receives a final light cold-rolled pass on polished rolls. This is a general purpose cold-rolled finish. It is commonly used for all but exceptionally difficult deep drawing applications. This finish is more readily polished than No. 1 or No. 2D Finish.

Bright Annealed Finish is a bright cold-rolled highly reflective finish retained by final annealing in a controlled atmosphere furnace. The purpose of the atmosphere is to prevent scaling or oxidation during annealing. The atmosphere is usually comprised of either dry hydrogen or a mixture of dry hydrogen and dry nitrogen (sometimes known as dissociated ammonia).

No. 3—For use as a finish-polished surface or as a semifinished-polished surface when it is required to receive subsequent finishing operations following fabrication. Where sheet or articles made from it will not be subjected to additional finishing or polishing operations, No. 4 finish is recommended.

No. 4—Widely used for restaurant equipment, kitchen equipment, store fronts, dairy equipment, etc. Following initial grinding with coarser abrasives, sheets are generally finished last with abrasives approximately 120 to 150 grit.

No. 6—Has a lower reflectivity than No. 4 finish. It is produced by Tampico brushing No. 4 finish sheets in a medium of abrasive and oil. It is used for architectural applications and ornamentation where high luster is undesirable; it is also used effectively to contrast with brighter finishes.

No. 7—Has a high degree of reflectivity. It is produced by buffing a finely ground surface, but the grit lines are not removed. It is chiefly used for architectural or ornamental purposes.

No. 8—The most reflective finish that is commonly produced. It is obtained by polishing with successively finer abrasives and buffing extensively with very fine buffing rouges. The surface is essentially free of grit lines from preliminary grinding operations. This finish is most widely used for press plate, as well as for small mirrors and reflectors.

12. Finish for Strip

12.1 The various types of finish procurable on cold-rolled strip products are:

12.1.1 No. 1 Finish—Cold rolled to specified thickness, annealed, and descaled.

12.1.2 No. 2 Finish—Same as No. 1 Finish, followed by a final light cold-roll pass, generally on highly polished rolls.

12.1.3 *Bright Annealed Finish*—A bright cold-rolled finish retained by final annealing in a controlled atmosphere furnace.

12.1.4 *Polished Finish*—Strip is also available in polished finishes such as No. 3 and No. 4, which are explained in [Note 1](#).

13. Finish for Plates

13.1 The types of finish available on plates are:

13.1.1 *Hot-Rolled or Cold-Rolled, and Annealed or Heat Treated, and Blast Cleaned or Pickled*—Condition and finish commonly preferred for corrosion-resisting and most heat-resisting applications, essentially a No. 1 Finish.

13.1.2 Hot Rolled or Cold rolled, annealed or heat treated, blast cleaned and/or ground.

13.1.3 Hot Rolled or Cold rolled, annealed or heat treated, blast cleaned and/or ground, and pickled.

14. Edges for Cold-Rolled Strip

14.1 The types of edges available on strip products are:

14.1.1 No. 1 Edge—A rolled edge, either round or square as specified.

14.1.2 No. 3 Edge—An edge produced by slitting.

14.1.3 No. 5 Edge—An approximately square edge produced by rolling or filing after slitting.

15. Permissible Variations in Dimensions and Weight

15.1 *Sheet*—Sheet shall conform to the permissible variations in dimensions specified in [Tables A1.1-A1.7](#) for materials produced to Specifications [B463](#), [B536](#), [B599](#), [B625](#), [B688](#), [B709](#) or [B718](#); and [Table A2.2](#) and [Table A2.4](#) for materials produced to Specifications [B333](#), [B434](#), [B435](#), [B575](#), [B582](#), [B620](#), [B814](#) or [B818](#); and [Table A3.3](#) and [Table A3.6](#) for materials produced to Specifications [B127](#), [B162](#), [B168](#), [B409](#), [B424](#), [B443](#), [B670](#), [B755](#) or [B872](#).

15.2 *Cold-Rolled Strip*—Cold-rolled strip shall conform to the permissible variations in dimensions specified in [Tables A1.1-A1.11](#) for materials produced to Specifications [B463](#), [B536](#), [B599](#), [B625](#), [B688](#), [B709](#) or [B718](#); [Table A2.2](#) and [Table A2.4](#) for materials produced to Specifications [B333](#), [B434](#), [B435](#), [B575](#), [B582](#), [B620](#), [B814](#) or [B818](#); and [Table A3.3](#) and [Table A3.6](#) for materials produced to Specifications [B127](#), [B162](#), [B168](#), [B409](#), [B424](#), [B443](#), [B670](#), [B755](#) or [B872](#).

15.3 *Plates*—Plates shall conform to the permissible variations in dimensions specified in [Tables A1.12-A1.18](#) for materials produced to Specifications [B463](#), [B536](#), [B599](#), [B625](#), [B688](#), [B709](#) or [B718](#); [Table A2.1](#) and [Table A2.3](#) for materials produced to Specifications [B333](#), [B434](#), [B435](#), [B575](#), [B582](#), [B620](#), [B814](#) or [B818](#); and [Table A3.1](#), [Table A3.2](#), [Table A3.4](#), [Table A3.5](#), and [Table A3.7](#) for materials produced to Specifications [B127](#), [B162](#), [B168](#), [B409](#), [B424](#), [B443](#), [B670](#), [B755](#) or [B872](#).

16. Workmanship

16.1 The material shall be of uniform quality consistent with good manufacturing and inspection practices. The material shall have no imperfections of a nature or degree, for the

type and quality ordered, that will adversely affect the stamping, forming, machining, or fabrication of finished parts.

16.2 *Sheet, Strip, and Plate*—Sheet, and strip with No. 1 finish and plate with hot-roll anneal or hot-roll anneal and pickle finish may be ground to remove surface imperfections, provided such grinding does not reduce the thickness or width at any point beyond the permissible variations in dimensions. An iron free abrasive wheel shall be used for such grinding and shall be operated in a speed ample to ensure that defective areas are cleanly cut out.

17. Repair of Plate by Welding

17.1 Repair of surface defects of plate, by welding, is permitted unless prohibited by other specifications or purchase order requirements.

17.2 Defect depth shall not exceed $\frac{1}{3}$ of the nominal thickness, and the total area shall not exceed 1 % of the plate surface area, unless prior approval from the purchaser is obtained.

17.3 Unacceptable imperfections shall be suitably prepared for welding by grinding or machining. Open clean defects, such as pits or impressions, may not require preparation.

17.4 The welding procedure and the welders or welding operators shall be qualified in accordance with Section IX of the ASME Code.

17.5 The welding consumables shall be compatible with both the chemistry and mechanical properties of the base material.

17.6 After repair welding, the welded area shall be ground smooth and blended uniformly to the surrounding surface.

17.7 Weld repair, if performed, shall be reported on the test report in accordance with Section 21.

18. Inspection

18.1 Inspection of the material by the purchaser's representative at the producing plant shall be made as agreed upon between the purchaser and the seller as part of the purchase order.

18.2 Unless otherwise specified in the contract or purchase order: (1) the seller is responsible for the performance of all the inspection and test requirements in this specification, (2) the seller may use his own or other suitable facilities for the performance of the inspection and testing, and (3) the purchaser shall have the right to perform any of the inspection and tests set forth in this specification. The manufacturer shall afford the purchaser's inspector all reasonable facilities necessary to satisfy him that the material is being furnished in accordance with the specification. Inspection by the purchaser shall not interfere unnecessarily with the manufacturer.

19. Rejection

19.1 Material that shows injurious imperfections per alloy specification subsequent to its acceptance at the purchaser's works will be rejected and the seller shall be notified.

20. Rehearing

20.1 Samples tested in accordance with the specification that represent rejected material shall be retained for a period agreed upon by purchaser and seller from the date of the notification to the seller of the rejection. In case of dissatisfaction with the results of the test, the seller may make claim for a rehearing within that time.

21. Material Test Report and Certification

21.1 A report of the result of all tests required by the product specification shall be supplied when required by the purchase order. This material test report shall reference the product specification designation and year date indicating that the material was manufactured, sampled, tested, and inspected in accordance with requirements of the product specification and has been found to meet those requirements. The material test report shall report the melting process when the purchase order requires either a specific type of melting or requires that the melting process used is to be reported.

21.1.1 The report shall indicate the type of material. If certifying that the material conforms to the requirements for more than one type of material, the manufacturer may indicate each type of material on the report, or may issue a separate report for each type of material.

21.1.2 When weld repair is performed, it shall be so stated on the test report, noting the alloy type of weld consumable used.

21.2 A signature is not required on the report. However, the document shall clearly identify the organization submitting the report.

21.3 A material test report, certificate of inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifier's facility. The content of the EDI transmitted document must meet the requirements of the invoked ASTM standard(s) and conform to any existing EDI agreement between the purchaser and the supplier. Notwithstanding the absence of a signature, the organization submitting the EDI transmission is responsible for the content of the report.

21.4 When finished material is supplied to a purchase order specifying the product specification, the organization supplying that material shall provide the purchaser with a copy of the original manufacturer's test report.

NOTE 2—Notwithstanding the absence of a signature, the organization submitting the report is responsible for the content of the report.

NOTE 3—The industry definition as invoked here is: EDI is the computer-to-computer exchange of business information in a standard format such as ANSI ASC X 12.

22. Packaging, Marking, and Loading

22.1 *For Commercial Procurement:*

22.1.1 *Marking*—Unless otherwise specified in the applicable material specification or the purchase order, marking shall be conducted as follows:

22.1.1.1 Sheet, strip, and plate shall be marked on one face, in the location indicated below with the specification designation number, type of material, material identification number,

and the name or mark of the manufacturer. The characters shall be of such size as to be clearly legible. The marking shall be sufficiently stable to withstand normal handling. Unless otherwise specified by the purchaser, the marking, at the producers option, may be done with (a) marking fluid (if a specific maximum impurity limit of designation elements in the marking fluid is required by the purchaser, it shall be so stated on the purchase order), (b) low-stress blunt-nosed continuous or low-stress blunt-nosed-interrupted-dot die stamp, (c) a vibratory tool with a minimum tip radius of 0.005 in (0.1 mm), or (d) electrochemical etching.

22.1.1.2 Flat sheet, strip in cut lengths, and plate shall be marked in two places near the ends or may be continuously line marked. Cut pieces from sheet, strip and plate, with both width and length, or diameter dimensions less than 48 in., may be marked in only one place.

22.1.1.3 Sheet, strip, and plate in coil form shall be marked near the outside end of the coil. The inside of the coil shall also be marked or shall have a tag or label attached and marked with the information of 22.1.1.1.

22.1.1.4 Material less than ¼ in. (6.4 mm) in thickness shall not be marked with die stamps.

22.1.1.5 Material that conforms completely with the requirements of two types of material within the ordering specification may be marked as both types of material provided that the manufacturer is certifying the material as meeting the requirements of each of the types of material. Such marking, if used may be part of the same marking as used for a single type of material, or may be a separate but similar marking immediately adjacent to the marking used for a single type of material.

22.1.1.6 The AIAG primary metals identification tag (AIAG B-5) may be used as a auxiliary method of identification in cases where a bar-coded identification tag is desired. Use of this method shall be by agreement between purchaser and supplier.

23. Keywords

23.1 nickel alloy; plate; sheet; strip

ANNEXES

(Mandatory Information)

A1. PERMISSIBLE VARIATIONS IN DIMENSIONS, ETC.—INCH-POUND (SI) UNITS

A1.1 Listed in Annex A1 are tables showing the permissible variations in dimensions expressed in inch-pound (SI) units of measurement applicable to material produced to Specifications

B463, B536, B599, B625, B688, B709 and B718, unless modified in accordance with Section 1.2 of this specification (Tables A1.1-A1.18).

TABLE A1.1 Permissible Variations in Thickness for Hot-Rolled Sheets in Cut Lengths, Cold-Rolled Sheet in Cut Lengths and Coils

Specified Thickness, ^A in. (mm)	Permissible Variations, Over and Under ^B	
	in.	mm
Over 0.145 (3.68) to less than ¾ (4.76)	0.014	0.36
Over 0.130 (3.30) to 0.145 (3.68), incl	0.012	0.30
Over 0.114 (2.90) to 0.130 (3.30), incl	0.010	0.25
Over 0.098 (2.49) to 0.114 (2.90), incl	0.009	0.23
Over 0.083 (2.11) to 0.098 (2.49), incl	0.008	0.20
Over 0.072 (1.83) to 0.083 (2.11), incl	0.007	0.18
Over 0.058 (1.47) to 0.072 (1.83), incl	0.006	0.15
Over 0.040 (1.02) to 0.058 (1.47), incl	0.005	0.13
Over 0.026 (0.66) to 0.040 (1.02), incl	0.004	0.10
Over 0.016 (0.41) to 0.026 (0.66), incl	0.003	0.08
Over 0.007 (0.18) to 0.016 (0.41), incl	0.002	0.05
Over 0.005 (0.13) to 0.007 (0.18), incl	0.0015	0.04
0.005 (0.13)	0.001	0.03

^A Thickness measurements are taken at least ¾ in. (9.52 mm) from the edge of the sheet.

^B Cold-rolled sheets in cut lengths and coils are produced in some type numbers and some widths and thickness to tolerances less than those shown in the table.

TABLE A1.2 Permissible Variations in Width and Length for Hot-Rolled and Cold-Rolled Resquared Sheets (Stretcher Leveled Standard of Flatness)

NOTE 1—Polished sheets with Finishes No. 4 and higher are produced to tolerances given in this table.

Specified Dimensions, in. (mm)	Tolerances		
	Over		Under
	in.	mm	
For thicknesses under 0.131 (3.33):			
Widths up to 48 (1219) excl	$\frac{1}{16}$	1.59	0
Widths 48 (1219) and over	$\frac{1}{8}$	3.18	0
Lengths up to 120 (3048) excl	$\frac{1}{16}$	1.59	0
Lengths 120 (3048) and over	$\frac{1}{8}$	3.18	0
For thicknesses 0.131 (3.33) and over:			
All widths and lengths	$\frac{1}{4}$	6.35	0

TABLE A1.3 Permissible Variations in Width for Hot-Rolled and Cold-Rolled Sheets not Resquared and Cold-Rolled Coils

Specified Thickness, in. (mm)	Tolerances for Specified Width, in. (mm)	
	24 (610) to 48 (1219), excl	48 (1219) and Over
Less than $\frac{3}{16}$ (4.76)	$\frac{1}{16}$ (1.59) over, 0 under	$\frac{1}{8}$ (3.18) over, 0 under

TABLE A1.4 Permissible Variations in Length for Hot-Rolled and Cold-Rolled Sheets Not Resquared

Length, ft (mm)	Tolerances, in. (mm)
Up to 10 (3048), incl	$\frac{1}{4}$ (6.35) over, 0
Over 10 (3048) to 20 (6096), incl	$\frac{1}{2}$ (12.70) over, 0 under

TABLE A1.5 Permissible Variations in Camber for Hot-Rolled and Cold-Rolled Sheets Not Resquared and Cold-Rolled Coils^A

Specified Width, in. (mm)	Tolerance per Unit Length of Any 8 ft (2438 mm), in. (mm)	
	24 (610) to 36 (914), incl	Over 36 (914)
	$\frac{1}{8}$ (3.18)	$\frac{3}{32}$ (2.38)

^A Camber is the greatest deviation of a side edge from a straight line and measurement is taken by placing an 8-ft (2438-mm) straightedge on the concave side and measuring the greatest distance between the sheet edge and the straightedge.

TABLE A1.6 Permissible Variations in Flatness for Hot-Rolled and Cold-Rolled Sheets Specified to Stretcher-Leveled Standard of Flatness (Not Including Hard Tempers of 2XX and 3XX Series)

Specified Thickness, in. (mm)	Width, in. (mm)	Length, in. (mm)	Flatness Tolerance, ^A in. (mm)
Under $\frac{3}{16}$ (4.76)	to 48 (1219), incl	to 96 (2438), incl	$\frac{1}{8}$ (3.18)
Under $\frac{3}{16}$ (4.76)	to 48 (1219), incl	over 96 (2438)	$\frac{1}{4}$ (6.35)
Under $\frac{3}{16}$ (4.76)	over 48 (1219)	to 96 (2438), incl	$\frac{1}{4}$ (6.35)
Under $\frac{3}{16}$ (4.76)	over 48 (1219)	over 96 (2438)	$\frac{1}{4}$ (6.35)

^A Maximum deviation from a horizontal flat surface.

TABLE A1.7 Permissible Variations in Diameter for Hot-Rolled and Cold-Rolled Sheets, Sheared Circles

Specified Thickness, in. (mm)	Tolerance Over Specified Diameter (No Tolerance Under), in. (mm)		
	Diameters Under 30 in. (762)	Diameters 30 (762) to 48 in. (1219)	Diameters Over 48 in. (1219)
0.0972 (2.46) and thicker	1/8 (3.18)	3/16 (4.76)	1/4 (6.35)
0.0971 (2.46) to 0.0568 (1.45), incl	3/32 (2.38)	5/32 (3.97)	7/32 (5.56)
0.0567 (1.45) and thinner	1/16 (1.59)	1/8 (3.18)	3/16 (4.76)

TABLE A1.8 Permissible Variations in Thickness for Cold-Rolled Strip in Coils and Cut Lengths

NOTE 1—Thickness measurements are taken at least 3/8 in. (9.52 mm) in from the edge of the strip, except on widths less than 1 in. (25.4 mm) the measurements should be taken at least 1/8 in. (3.18 mm) from the strip edge.

NOTE 2—The tolerance in this table include crown tolerances.

Specified Thickness, in. (mm)	Thickness Tolerances, for the Thickness and Widths Given, Over and Under, in. (mm)		
	Width, in. (mm)		
	3/16 (4.76) to 6 (152), incl	Over 6 (152) to 12 (305), incl	Over 12 (305) to 24 (610), excl
	Thickness Tolerances ^A		
0.005 (0.13) to 0.010 (0.25), incl	10 %	10 %	10 %
Over 0.010 (0.25) to 0.011 (0.28), incl	0.0015 (0.04)	0.0015 (0.04)	0.0015 (0.04)
Over 0.011 (0.28) to 0.013 (0.33), incl	0.0015 (0.04)	0.0015 (0.04)	0.002 (0.05)
Over 0.013 (0.33) to 0.017 (0.43), incl	0.0015 (0.04)	0.002 (0.05)	0.002 (0.05)
Over 0.017 (0.43) to 0.020 (0.51), incl	0.0015 (0.04)	0.002 (0.05)	0.0025 (0.06)
Over 0.020 (0.51) to 0.029 (0.74), incl	0.002 (0.05)	0.0025 (0.06)	0.0025 (0.06)
Over 0.029 (0.74) to 0.035 (0.89), incl	0.002 (0.05)	0.003 (0.08)	0.003 (0.08)
Over 0.035 (0.89) to 0.050 (1.27), incl	0.0025 (0.06)	0.0035 (0.09)	0.0035 (0.09)
Over 0.050 (1.27) to 0.069 (1.75), incl	0.003 (0.08)	0.0035 (0.09)	0.0035 (0.09)
Over 0.069 (1.75) to 0.100 (2.54), incl	0.003 (0.08)	0.004 (0.10)	0.005 (0.13)
Over 0.100 (2.54) to 0.125 (2.98), incl	0.004 (0.10)	0.0045 (0.11)	0.005 (0.13)
Over 0.125 (2.98) to 0.161 (4.09), incl	0.0045 (0.11)	0.0045 (0.11)	0.005 (0.13)
Over 0.161 (4.09) to under 3/16 (4.76)	0.005 (0.13)	0.005 (0.13)	0.006 (0.15)

^A Thickness tolerances given in in. (mm) unless otherwise indicated.

TABLE A1.9 Permissible Variations in Width for Cold-Rolled Strip in Coils and Cut Lengths for Edge Nos. 1 and 5

Specified Edge No.	Width, in. (mm)	Thickness, in. (mm)	Width Tolerance for Thickness and Width Given, in. (mm)	
			Over	Under
1 and 5	3/32 (7.14) and under	1/16 (1.59) and under	0.005 (0.13)	0.005 (0.13)
1 and 5	over 3/32 (7.14) to 3/4 (19.05), incl	3/32 (2.38) and under	0.005 (0.13)	0.005 (0.13)
1 and 5	over 3/4 (19.05) to 5 (127), incl	1/8 (3.18) and under	0.005 (0.13)	0.005 (0.13)
5	over 5 (127.00) to 9 (228.60), incl	1/8 (3.18) to 0.008 (0.20), incl	0.010 (0.25)	0.010 (0.25)
5	over 9 (228.60) to 20 (508.00), incl	0.105 (2.67) to 0.015 (0.38)	0.010 (0.25)	0.010 (0.25)
5	over 20 (508.00)	0.080 (2.03) to 0.023 (0.58)	0.015 (0.38)	0.015 (0.38)

TABLE A1.10 Permissible Variations in Width for Cold-Rolled Strip in Coils and Cut Lengths for Edge No. 3

Specified Thickness, in. (mm)	Width Tolerance, Over and Under, for Thickness and Width Given, in. (mm)					
	Under 1/2 (12.70) to 3/16 (4.76), incl	1/2 (12.70) to 6 (152.40), incl	Over 6 (152.40) to 9 (228.60), incl	Over 9 (228.60) to 12 (304.80), incl	Over 12 (304.80) to 20 (508.00), incl	Over 20 (508.00) to 24 (609.60), incl
Under 3/16 (4.76) to 0.161 (4.09), incl	...	0.016 (0.41)	0.020 (0.51)	0.020 (0.51)	0.031 (0.79)	0.031 (0.79)
0.160 (4.06) to 0.100 (2.54), incl	0.010 (0.25)	0.010 (0.25)	0.016 (0.41)	0.016 (0.41)	0.020 (0.51)	0.020 (0.51)
0.099 (2.51) to 0.069 (1.75), incl	0.008 (0.20)	0.008 (0.20)	0.010 (0.25)	0.010 (0.25)	0.016 (0.41)	0.020 (0.51)
0.068 (1.73) and under	0.005 (0.13)	0.005 (0.13)	0.005 (0.13)	0.010 (0.25)	0.016 (0.41)	0.020 (0.51)

TABLE A1.11 Permissible Variations in Camber for Cold-Rolled Strip in Coils and Cut Lengths^A

Specified Width, in. (mm)	Tolerance per Unit Length of Any 8 ft (2438 mm), in. (mm)
To 1½ (38.10), incl	½ (12.70)
Over 1½ (38.10) to 24 (609.60), excl	¼ (6.35)

^A Camber is the deviation of a side edge from a straight line and measurement is taken by placing an 8-ft (2438-mm) straightedge on the concave side and measuring the greatest distance between the strip edge and the straightedge.

TABLE A1.12 Permissible Variations in Thickness for Plates^{A,B}

Specified Thickness, in. (mm)	Width, in. (mm)			
	To 84 (2134), incl	Over 84 (2134) to 120 (3048), incl	Over 120 (3048) to 144 (3658), incl	Over 144 (3658)
	Tolerance Over Specified Thickness, ^C in. (mm)			
⅜ (4.76) to ⅝ (9.52), excl	0.045 (1.14)	0.050 (1.27)	...	...
⅝ (9.52) to ¾ (19.05), excl	0.055 (1.40)	0.060 (1.52)	0.075 (1.90)	0.090 (2.29)
¾ (19.05) to 1 (25.40), excl	0.060 (1.52)	0.065 (1.65)	0.085 (2.16)	0.100 (2.54)
1 (25.40) to 2 (50.80), excl	0.070 (1.78)	0.075 (1.90)	0.095 (2.41)	0.115 (2.92)
2 (50.80) to 3 (76.20), excl	0.125 (3.18)	0.150 (3.81)	0.175 (4.44)	0.200 (5.08)
3 (76.20) to 4 (101.6), excl	0.175 (4.44)	0.210 (5.33)	0.245 (6.22)	0.280 (7.11)
4 (101.6) to 6 (152.4), excl	0.250 (6.35)	0.300 (7.62)	0.350 (8.89)	0.400 (10.16)
6 (152.4) to 8 (203.2), excl	0.350 (8.89)	0.420 (10.67)	0.490 (12.45)	0.560 (14.22)
8 (203.2) to 10 (254.0), excl	0.450 (11.43)	0.540 (13.72)	0.630 (16.00)	...

^A Thickness is measured along the longitudinal edges of the plate at least ⅜ in. (9.52 mm), but not more than 3 in. (76.20 mm), from the edge.

^B For plates up to 10 in. (254.0 mm), excl, in thickness, the tolerance under the specified thickness is 0.010 in. (0.25 mm).

^C For circles, the over thickness tolerances in this table apply to the diameter of the circle corresponding to the width ranges shown. For plates of irregular shape, the over thickness tolerances apply to the greatest width corresponding to the width ranges shown.

TABLE A1.13 Permissible Variations in Width and Length for Rectangular Sheared Mill Plates and Universal Mill Plates

Width, in. (mm)	Length, in. (mm)	Tolerances Over Specified Width and Length for Given Width, Length, and Thickness, ^A in. (mm)					
		Under ⅜ in. (9.52 mm) in Thickness		⅜ (9.52) to ½ (12.70 mm) in., incl, in Thickness		Over ½ (12.70 mm) to 1 in. (25.40 mm) in Thickness	
		Width	Length	Width	Length	Width	Length
48 (1219) and under	144 (3658) and under	⅛ (3.18)	⅜ (4.76)	⅜ (4.76)	¼ (6.35)	⅝ (7.94)	⅝ (9.52)
Over 48 (1219) to 60 (1524), incl		⅜ (4.76)	¼ (6.35)	¼ (6.35)	⅝ (7.94)	⅝ (9.52)	⅞ (11.11)
Over 60 (1524) to 84 (2134), incl		¼ (6.35)	⅝ (7.94)	⅝ (7.94)	⅝ (9.52)	⅞ (11.11)	1 (12.70)
Over 84 (2134) to 108 (2743), incl		⅝ (7.94)	⅝ (9.52)	⅝ (9.52)	⅞ (11.11)	1 (12.70)	⅞ (14.29)
Over 108 (2743)		⅝ (9.52)	⅞ (11.11)	⅞ (11.11)	1 (12.70)	⅞ (15.88)	1⅛ (17.46)
48 (1219) and under	over 144 (3658) to 240 (6096)	⅜ (4.76)	⅝ (9.52)	¼ (6.35)	½ (12.70)	⅝ (7.94)	⅝ (15.88)
Over 48 (1219) to 60 (1524), incl		¼ (6.35)	⅞ (11.11)	⅝ (7.94)	⅝ (15.88)	⅝ (9.52)	¾ (19.05)
Over 60 (1524) to 84 (2134), incl		⅝ (9.52)	1 (12.70)	⅞ (11.11)	1⅛ (17.46)	1 (12.70)	¾ (19.05)
Over 84 (2134) to 108 (2743), incl		⅞ (11.11)	⅞ (14.29)	1 (12.70)	¾ (19.05)	⅝ (15.88)	⅞ (22.22)
Over 108 (2743)		1 (12.70)	⅝ (15.88)	⅝ (15.88)	⅞ (22.22)	1⅛ (17.46)	1 (25.40)
48 (1219) and under	over 240 (6096) to 360 (9144)	¼ (6.35)	1 (12.70)	⅝ (7.94)	⅝ (15.88)	⅝ (9.52)	¾ (19.05)
Over 48 (1219) to 60 (1524), incl		⅝ (7.94)	⅝ (15.88)	⅝ (9.52)	¾ (19.05)	1 (12.70)	¾ (19.05)
Over 60 (1524) to 84 (2134), incl		⅞ (11.11)	1⅛ (17.46)	1 (12.70)	¾ (19.05)	⅝ (15.88)	⅞ (22.22)
Over 84 (2134) to 108 (2743), incl		⅞ (14.29)	¾ (19.05)	⅝ (15.88)	⅞ (22.22)	¾ (19.05)	1 (25.40)
Over 108 (2743)		⅝ (15.88)	⅞ (22.22)	1⅛ (17.46)	1 (25.40)	⅞ (22.22)	1 (25.40)
60 (1524) and under	over 360 (9144) to 480 (12192)	⅞ (11.11)	1⅞ (28.58)	1 (12.70)	1¼ (31.75)	⅝ (15.88)	1⅝ (34.92)
Over 60 (1524) to 84 (2134), incl		1 (12.70)	1¼ (31.75)	⅝ (15.88)	1⅝ (34.92)	¾ (19.05)	1½ (38.10)
Over 84 (2134) to 108 (2743), incl		⅞ (14.29)	1¼ (31.75)	¾ (19.05)	1⅝ (34.92)	⅞ (22.22)	1½ (38.10)
Over 108 (2743)		¾ (19.05)	1⅝ (34.92)	⅞ (22.22)	1½ (38.10)	1 (25.40)	1⅝ (41.28)
60 (1524) and under	over 480 (12192) to 600 (15240)	⅞ (11.11)	1¼ (31.75)	1 (12.70)	1½ (38.10)	⅝ (15.88)	1⅝ (41.28)
Over 60 (1524) to 84 (2134), incl		1 (12.70)	1⅝ (34.92)	⅝ (15.88)	1½ (38.10)	¾ (19.05)	1⅝ (41.28)
Over 84 (2134) to 108 (2743), incl		⅝ (15.88)	1⅝ (34.92)	¾ (19.05)	1½ (38.10)	⅞ (22.22)	1⅝ (41.28)
Over 108 (2743)		¾ (19.05)	1½ (38.10)	⅞ (22.22)	1⅝ (41.28)	1 (25.40)	1¾ (44.45)
60 (1524) and under	over 600 (15240)	1 (12.70)	1¾ (44.45)	⅝ (15.88)	1⅞ (47.62)	¾ (19.05)	1⅞ (47.62)
Over 60 (1524) to 84 (2134), incl		⅝ (15.88)	1¾ (44.45)	¾ (19.05)	1⅞ (47.62)	⅞ (22.22)	1⅞ (47.62)
Over 84 (2134) to 108 (2743), incl		⅝ (15.88)	1¾ (44.45)	¾ (19.05)	1⅞ (47.62)	⅞ (22.22)	1⅞ (47.62)
Over 108 (2743)		⅞ (22.22)	1¾ (44.45)	1 (25.40)	2 (50.80)	1⅞ (28.58)	2¼ (57.15)

^A The tolerance under specified width and length is ¼ in. (6.35 mm).

TABLE A1.14 Permissible Variations in Flatness for Annealed Plates

NOTE 1—Tolerances in this table apply to plates up to 15 ft (4572 mm) in length, or to any 15 ft (4572 mm) of longer plates.

NOTE 2—If the longer dimension is under 36 in. (914 mm), the tolerance is not greater than ¼ in. (6.35 mm).

NOTE 3—For plates with specified minimum yield strengths of 35 ksi (240 MPa) or more, and all steels of Specification A693, the permissible variations are increased to 1½ times the amounts shown below.

Specified Thickness, in. (mm)	Flatness Tolerance (Deviation from a Horizontal Flat Surface) for Thicknesses and Widths Given, in. (mm)								
	Width, in. (mm)								
	48 (1219) or Under	Over 48 (1219) to 60 (1524), excl	60 (1524) to 72 (1829), excl	72 (1829) to 84 (2134), excl	84 (2134) to 96 (2438), excl	96 (2438) to 108 (2743), excl	108 (2743) to 120 (3048), excl	120 (3048) to 144 (3658), excl	144 (3658) and Over
⅜ (4.76) to ¼ (6.35), excl	¾ (19.05)	1 ⅛ (26.99)	1 ¼ (31.75)	1 ⅝ (34.92)	1 ¾ (41.28)	1 ¾ (41.28)	1 ⅞ (47.62)	2 (50.80)	...
¼ (6.35) to ⅝ (9.52), excl	1 ⅛ (17.46)	¾ (19.05)	1 ⅝ (23.81)	1 ⅞ (28.58)	1 ¾ (34.92)	1 ⅞ (36.51)	1 ⅞ (39.69)	1 ⅞ (47.62)	...
⅝ (9.52) to ½ (12.70), excl	½ (12.70)	⅞ (14.29)	1 ⅛ (17.46)	¾ (19.05)	1 ⅞ (23.81)	1 ⅞ (28.58)	1 ¼ (31.75)	1 ⅞ (36.51)	1 ¾ (44.45)
½ (12.70) to ¾ (19.05), excl	½ (12.70)	⅞ (14.29)	⅝ (15.88)	⅝ (15.88)	1 ⅜ (20.64)	1 ⅞ (28.58)	1 ⅞ (28.58)	1 ⅞ (28.58)	1 ⅞ (34.92)
¾ (19.05) to 1 (25.40), excl	½ (12.70)	⅞ (14.29)	⅝ (15.88)	⅝ (15.88)	¾ (19.05)	1 ⅜ (20.64)	1 ⅞ (23.81)	1 (25.40)	1 ⅞ (28.58)
1 (25.40) to 1 ½ (38.10), excl	½ (12.70)	⅞ (14.29)	⅞ (14.29)	⅞ (14.29)	1 ⅞ (17.46)	1 ⅞ (17.46)	1 ⅞ (17.46)	¾ (19.05)	1 (25.40)
1 ½ (38.10) to 4 (101.60), excl	⅝ (7.94)	¾ (9.52)	⅞ (11.11)	½ (12.70)	⅝ (15.88)	¾ (19.05)	⅞ (22.22)	1 (25.40)	1 (25.40)
4 (101.60) to 6 (152.40), excl	¾ (9.52)	⅞ (11.11)	⅞ (14.29)	⅝ (15.88)	¾ (19.05)	1 ⅞ (23.81)	1 ⅞ (28.58)	1 ¼ (31.75)	1 ¼ (31.75)

TABLE A1.15 Permissible Variations in Camber for Sheared Mill and Universal Mill Plates^A

Maximum camber = ⅛ in. in any 5 ft
= 3.18 mm in any 1.524 m

^A Camber is the deviation of a side edge from a straight line, and measurement is taken by placing a 5-ft straightedge on the concave side and measuring the greatest distance between the plate and the straightedge.

TABLE A1.16 Permissible Variations in Diameter for Circular Plates

Specified Diameter, in. (mm)	Tolerance Over Specified Diameter for Given Diameter and Thickness, ^A in. (mm)		
	To ⅝ (9.52) in., excl in Thickness	⅝ (9.52) to ⅞ (15.88) in., excl in Thickness	⅞ in. (15.88) and Over in Thickness ^B
To 60 (1524), excl	¼ (6.35)	⅝ (9.52)	½ (12.70)
60 (1524 mm) to 84 (2134 mm), excl	⅝ (7.94)	⅞ (11.11)	⅞ (14.29)
84 (2134 mm) to 108 (2743 mm), excl	¾ (9.52)	½ (12.70)	⅞ (15.88)
108 (2743 mm) to 180 (4572 mm), excl	⅞ (11.11)	⅞ (14.29)	1 ⅛ (17.46)

^A No tolerance under.

^B Circular and sketch plates over ⅞ in. (15.88 mm) in thickness are not commonly sheared but are machined or flame cut.

TABLE A1.17 Torch Cutting Tolerances^A and Recommended Cleanup Allowance for Rectangular Plates, Circles, Rings, and Sketches

Specified Thickness, in.	Tolerance, in.		Cleanup Allowance ^B per Edge, in.
	Outside Dimension	Inside Dimension	
2 and under	+⅜, -0	-⅜, +0	±¼
Over 2 to 3 incl	+½, -0	-½, +0	±⅝
Over 3 to 6 incl	+¾, -0	-¾, +0	±½

^A Tolerances to apply unless otherwise agreed. Note that for some applications user may wish to specify minus rather than plus tolerance or vice versa.

^B Recommended cleanup allowance which, unless otherwise specified, will be applied by supplier to purchasers ordered size.

TABLE A1.18 Permissible Variations in Abrasive Cutting Width and Length for Plates

Specified Thickness, in. (mm)	Tolerance over Specified Width and Length ^A	
	Width	Length
Up to 1 (25.40), incl	1/8 (3.18)	1/8 (3.18)
1 (25.40) to 2 (50.80), incl	3/16 (4.76)	3/16 (4.76)
2 (50.80) to 3 (76.20), incl	1/4 (6.35)	1/4 (6.35)
3 (76.20) to 4 (101.6), incl ^B	5/16 (7.94)	5/16 (7.94)

^A The tolerances under specified width and length are 1/8 in. (3.18 mm).

^B Width and length tolerances for abrasive cut plates over 4 in. (101.6 mm) thick are not included in the table; consult producer.

A2. PERMISSIBLE VARIATIONS IN DIMENSIONS, ETC.—INCH-POUND (SI) UNITS

A2.1 Listed in **Annex A1** are tables showing the permissible variations in dimensions expressed in inch-pound (SI) units of measurement applicable to material produced to Specifications

B333, B434, B435, B575, B582, B620, B814 or B818, unless modified in accordance with Section 1.2 of this specification (**Tables A2.1-A2.4**).

TABLE A2.1 Permissible Variations in Thickness of Plate^A

Specified Thickness, in. (mm)	Permissible Variations in Thickness, in. (mm) ^{B,C}	
	+	–
3/16 to 7/32 (4.762 to 5.556), incl	0.021 (0.53)	0.010 (0.25)
Over 7/32 to 1/4 (5.556 to 6.350), incl	0.024 (0.61)	0.010 (0.25)
Over 1/4 to 3/8 (6.350 to 9.525), incl	0.027 (0.69)	0.010 (0.25)
Over 3/8 to 1/2 (9.525 to 12.70), incl	0.030 (0.76)	0.010 (0.25)
Over 1/2 to 5/8 (12.70 to 15.88), incl	0.035 (0.89)	0.010 (0.25)
Over 5/8 to 3/4 (15.88 to 19.05), incl	0.040 (1.02)	0.010 (0.25)
Over 3/4 to 7/8 (19.05 to 22.25), incl	0.045 (1.14)	0.010 (0.25)
Over 7/8 to 1 (22.25 to 25.4), incl	0.050 (1.27)	0.010 (0.25)
Over 1 to 2 1/2 (25.4 to 63.5), incl	5 ^D	0.010 (0.25)

^A Applicable to plate 48 in. (1.22 m) and under in width.

^B Measured 3/8 in. (9.525 mm) or more from any edge.

^C Buffing or grinding for removal of light surface imperfections shall be permitted. The depth of such buffed or ground areas shall not exceed the minimum tolerance thickness.

^D Expressed as percent of thickness.

TABLE A2.2 Permissible Variations in Thickness of Sheet^A and Strip

Specified Thickness, in. (mm)	Permissible Variations in Thickness, in ^{B,C} (mm) (All Widths)	
	+	–
0.020 to 0.034 (0.51 to 0.86), incl	0.004 (0.10)	0.004 (0.10)
Over 0.034 to 0.056 (0.86 to 1.42), incl	0.005 (0.13)	0.005 (0.13)
Over 0.056 to 0.070 (1.42 to 1.78), incl	0.006 (0.15)	0.006 (0.15)
Over 0.070 to 0.078 (1.78 to 1.98), incl	0.007 (0.18)	0.007 (0.18)
Over 0.078 to 0.093 (1.98 to 2.36), incl	0.008 (0.20)	0.008 (0.20)
Over 0.093 to 0.109 (2.36 to 2.77), incl	0.009 (0.23)	0.009 (0.23)
Over 0.109 to 0.125 (2.77 to 3.18), incl	0.010 (0.25)	0.010 (0.25)
Over 0.125 to 0.140 (3.18 to 3.56), incl	0.013 (0.33)	0.010 (0.25)
Over 0.140 to 0.171 (3.56 to 4.34), incl	0.016 (0.41)	0.010 (0.25)
Over 0.171 to 0.187 (4.34 to 4.75), incl	0.018 (0.46)	0.010 (0.25)

^A Applicable to sheet 48 in. (1.22 m) and under in width.

^B Measured $\frac{3}{8}$ in. (9.525 mm) or more from any edge.

^C Buffing for removal of light surface imperfections shall be permitted. The depth of such buffed areas shall not exceed the permissible minus variation.

TABLE A2.3 Permissible Variations in Width and Length of Sheared, Torch-Cut, or Abrasive-Cut Rectangular Plate

Specified Thickness	Permissible Variations in Widths and Lengths for Dimensions Given, in. (mm)			
	Up to 30 (760), incl		Over 30 (760)	
	+	–	+	–
Inches				
Sheared:				
$\frac{3}{16}$ to $\frac{5}{16}$, excl	$\frac{3}{16}$	$\frac{1}{8}$	$\frac{1}{4}$	$\frac{1}{8}$
$\frac{5}{16}$ to $\frac{1}{2}$, incl	$\frac{1}{4}$	$\frac{1}{8}$	$\frac{3}{8}$	$\frac{1}{8}$
Abrasive-cut:				
$\frac{3}{16}$ to $1\frac{1}{2}$, incl	$\frac{1}{16}$	$\frac{1}{16}$	$\frac{1}{16}$	$\frac{1}{16}$
Over $1\frac{1}{2}$ to $2\frac{1}{2}$, incl	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$
Torch-cut:^A				
$\frac{3}{16}$ to 2 excl	$\frac{1}{2}$	0	$\frac{1}{2}$	0
2 to 3 incl	$\frac{5}{8}$	0	$\frac{5}{8}$	0
Millimetres				
Sheared:				
4.76 to 7.94, excl	4.76	3.18	6.35	3.18
7.94 to 12.70, incl	6.35	3.18	9.52	3.18
Abrasive-cut:				
4.76 to 38.1, incl	1.59	1.59	1.59	1.59
Over 38.1 to 63.5, incl	3.18	3.18	3.18	3.18
Torch-cut:^A				
4.8 to 50.8 excl	12.7	0	12.7	0
50.8 to 76.2 incl	15.9	0	15.9	0

^A The tolerance spread shown for torch-cutting may be obtained all on the minus side, or divided between the plus and the minus side if so specified by the purchaser.

TABLE A2.4 Permissible Variations in Width of Sheet and Strip

Specified Thickness, in. (mm)	Specified Width, in. (mm)	Permissible Variations in Specified Width, in. (mm)	
		+	–
Sheet			
0.187 (4.76) and under	2 (50.8) and over	0.125 (3.18)	0
Strip (Slit Edges)			
Over 0.020 to 0.075 (0.51 to 1.90), incl	24 (610) and under	0.007 (0.18)	0.007 (0.18)
Over 0.075 to 0.100 (1.90 to 2.54), incl	24 (610) and under	0.009 (0.23)	0.009 (0.23)
Over 0.100 to 0.125 (2.54 to 3.18), incl	24 (610) and under	0.012 (0.30)	0.012 (0.30)

A3. PERMISSIBLE VARIATIONS IN DIMENSIONS, ETC.—INCH-POUND (SI) UNITS

A3.1 Listed in **Annex A1** are tables showing the permissible variations in dimensions expressed in inch-pound (SI) units of measurement applicable to material produced to Specifications

B127, B162, B168, B409, B424, B443, B670, B755 or B872, unless modified in accordance with Section 1.2 of this specification (**Tables A3.1-A3.7**).

TABLE A3.1 Permissible Variations in Thickness and Overweight of Rectangular Plates

NOTE 1—All plates shall be ordered to thickness and not to weight per square foot. No plates shall vary more than 0.01 in. (0.3 mm) under the thickness ordered, and the overweight of each lot^A in each shipment shall not exceed the amount given in the table. Spot grinding is permitted to remove surface imperfections, such spots not to exceed 0.01 in. (0.3 mm) under the specified thickness.

Specified Thickness, in. (mm)	Permissible Excess in Average Weight ^{B,C} per Square Foot of Plates for Widths Given in Inches (Millimetres) Expressed in Percent of Nominal Weights									
	Under 48 (1220)	48 to 60 (1220 to 1520), excl	60 to 72 (1520 to 1830), excl	72 to 84 (1830 to 2130), excl	84 to 96 (2130 to 2440), excl	96 to 108 (2440 to 2740), excl	108 to 120 (2740 to 3050), excl	120 to 132 (3050 to 3350), excl	132 to 144 (3350 to 3660), excl	144 to 160 (3660 to 4070), excl
3/16 to 5/16 (4.8 to 7.9), excl	9.0	10.5	12.0	13.5	15.0	16.5	18.0	...	...	...
5/16 to 3/8 (7.9 to 9.5), excl	7.5	9.0	10.5	12.0	13.5	15.0	16.5	18.0	...	...
3/8 to 7/16 (9.5 to 11.1), excl	7.0	7.5	9.0	10.5	12.0	13.5	15.0	16.5	18.0	19.5
7/16 to 1/2 (11.1 to 12.7), excl	6.0	7.0	7.5	9.0	10.5	12.0	13.5	15.0	16.5	18.0
1/2 to 5/8 (12.7 to 15.9), excl	5.0	6.0	7.0	7.5	9.0	10.5	12.0	13.5	15.0	16.5
5/8 to 3/4 (15.9 to 19.1), excl	4.5	5.5	6.0	7.0	7.5	9.0	10.5	12.0	13.5	15.0
3/4 to 1 (19.1 to 25.4), excl	4.0	4.5	5.5	6.0	7.0	7.5	9.0	10.5	12.0	13.5
1 to 2 (25.4 to 50.8), incl	4.0	4.0	4.5	5.5	6.0	7.0	7.5	9.0	10.5	12.0

^A The term "lot" applied to this table means all of the plates of each group width and each group thickness.

^B The permissible overweight for lots of circular and sketch plates shall be 25 % greater than the amounts given in this table.

^C The weight of individual plates shall not exceed the nominal weight by more than 1 1/4 times the amount given in the table and Footnote B.

TABLE A3.2 Permissible Variations in Thickness for Rectangular Plates Over 2 in. (51 mm) in Thickness

NOTE 1—Permissible variation under specified thickness, 0.01 in. (0.3 mm).

Specified Thickness, in. (mm)	Permissible Variations, in. (mm), over Specified Thickness for Widths Given, in. (mm)					
	To 36 (915), excl	36 to 60 (915 to 1520), excl	60 to 84 (1520 to 2130), excl	84 to 120 (2130 to 3050), excl	120 to 132 (3050 to 3350), excl	132 (3350 and over)
Over 2 to 3 (51 to 76.0), incl	1/16 (1.6)	3/32 (2.4)	7/64 (2.8)	1/8 (3.2)	1/8 (3.2)	9/64 (3.6)
3 to 4 (76.0 to 102.0), incl	5/64 (2.0)	3/32 (2.4)	7/64 (2.8)	1/8 (3.2)	1/8 (3.2)	9/64 (3.6)

TABLE A3.3 Permissible Variations in Thickness of Sheet and Strip
(Permissible Variations, Plus and Minus, in Thickness, in. (mm), for Widths Given in in. (mm))

Specified Thickness, in. (mm), incl	Sheet ^A			
	Hot-Rolled		Cold-Rolled	
	48 (1220) and Under	Over 48 to 60 (1220 to 1520), incl	48 (1220) and Under	Over 48 to 60 (1220 to 1520), incl
0.018 to 0.025 (0.5 to 0.6)	0.003 (0.08)	0.004 (0.10)	0.002 (0.05)	0.003 (0.08)
Over 0.025 to 0.034 (0.6 to 0.9)	0.004 (0.10)	0.005 (0.13)	0.003 (0.08)	0.004 (0.10)
Over 0.034 to 0.043 (0.9 to 1.1)	0.005 (0.13)	0.006 (0.15)	0.004 (0.10)	0.005 (0.13)
Over 0.043 to 0.056 (1.1 to 1.4)	0.005 (0.13)	0.006 (0.15)	0.004 (0.10)	0.005 (0.13)
Over 0.056 to 0.070 (1.4 to 1.8)	0.006 (0.15)	0.007 (0.18)	0.005 (0.13)	0.006 (0.15)
Over 0.070 to 0.078 (1.8 to 1.9)	0.007 (0.18)	0.008 (0.20)	0.006 (0.15)	0.007 (0.18)
Over 0.078 to 0.093 (1.9 to 2.4)	0.008 (0.20)	0.009 (0.23)	0.007 (0.18)	0.008 (0.20)
Over 0.093 to 0.109 (2.4 to 2.8)	0.009 (0.23)	0.010 (0.25)	0.007 (0.18)	0.009 (0.23)
Over 0.109 to 0.125 (2.8 to 3.2)	0.010 (0.25)	0.012 (0.31)	0.008 (0.20)	0.010 (0.25)
Over 0.125 to 0.140 (3.2 to 3.6)	0.012 (0.31)	0.014 (0.36)	0.008 (0.20)	0.010 (0.25)
Over 0.140 to 0.171 (3.6 to 4.3)	0.014 (0.36)	0.016 (0.41)	0.009 (0.23)	0.012 (0.31)
Over 0.171 to 0.187 (4.3 to 4.8)	0.015 (0.38)	0.017 (0.43)	0.010 (0.25)	0.013 (0.33)
Over 0.187 to 0.218 (4.8 to 5.5)	0.017 (0.43)	0.019 (0.48)	0.011 (0.28)	0.015 (0.38)
Over 0.218 to 0.234 (5.5 to 5.9)	0.018 (0.46)	0.020 (0.51)	0.012 (0.31)	0.016 (0.41)
Over 0.234 to 0.250 (5.9 to 6.4)	0.020 (0.51)	0.022 (0.56)	0.013 (0.33)	0.018 (0.46)
Cold-Rolled ^{A,B}				
Specified Thickness, in. (mm), incl	Widths 12 in. (305 mm) and under, plus and minus			
Up to 0.050 (1.27), incl	0.0015 (0.038)			
Over 0.050 to 0.093 (1.27 to 2.39)	0.0025 (0.063)			
Over 0.093 to 0.125 (2.39 to 3.18)	0.004 (0.11)			

^A Measured $\frac{3}{16}$ in. (9.5 mm) or more from either edge except for strip under 1 in. (25.4 mm) in width which is measured at any place.

^B Standard sheet tolerances apply for thicknesses over 0.125 in. (3.2 mm) and for all thicknesses of strip over 12 in. (305 mm) wide.

TABLE A3.4 Permissible Variations in Width^A of Sheared, Plasma Torch-Cut, and Abrasive-Cut Rectangular Plate^{B,C}

Specified Thickness	Permissible Variations in Widths for Widths Given, in. (mm)									
	Up to 30 (760), incl		Over 30 to 72 (760 to 1830), incl		Over 72 to 108 (1830 to 2740), incl		Over 108 to 144 (2740 to 3660), incl		Over 144 to 160 (3660 to 4070), incl	
	Plus	Minus	Plus	Minus	Plus	Minus	Plus	Minus	Plus	Minus
Inches										
Sheared: ^D										
$\frac{3}{16}$ to $\frac{5}{16}$, excl	$\frac{3}{16}$	$\frac{1}{8}$	$\frac{1}{4}$	$\frac{1}{8}$	$\frac{3}{8}$	$\frac{1}{8}$	$\frac{1}{2}$	$\frac{1}{8}$	...	...
$\frac{5}{16}$ to $\frac{1}{2}$, excl	$\frac{1}{4}$	$\frac{1}{8}$	$\frac{3}{8}$	$\frac{1}{8}$	$\frac{3}{8}$	$\frac{1}{8}$	$\frac{1}{2}$	$\frac{1}{8}$	$\frac{5}{8}$	$\frac{1}{8}$
$\frac{1}{2}$ to $\frac{3}{4}$, excl	$\frac{3}{8}$	$\frac{1}{8}$	$\frac{3}{8}$	$\frac{1}{8}$	$\frac{1}{2}$	$\frac{1}{8}$	$\frac{5}{8}$	$\frac{1}{8}$	$\frac{3}{4}$	$\frac{1}{8}$
$\frac{3}{4}$ to 1, excl	$\frac{1}{2}$	$\frac{1}{8}$	$\frac{1}{2}$	$\frac{1}{8}$	$\frac{5}{8}$	$\frac{1}{8}$	$\frac{3}{4}$	$\frac{1}{8}$	$\frac{7}{8}$	$\frac{1}{8}$
1 to $1\frac{1}{4}$, incl	$\frac{5}{8}$	$\frac{1}{8}$	$\frac{5}{8}$	$\frac{1}{8}$	$\frac{3}{4}$	$\frac{1}{8}$	$\frac{7}{8}$	$\frac{1}{8}$	1	$\frac{1}{8}$
Abrasive-cut: ^{E,F}										
$\frac{3}{16}$ to $1\frac{1}{4}$, incl	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$	$\frac{1}{8}$
Over $1\frac{1}{4}$ to $2\frac{3}{4}$, incl	$\frac{3}{16}$	$\frac{1}{8}$	$\frac{3}{16}$	$\frac{1}{8}$	$\frac{3}{16}$	$\frac{1}{8}$	$\frac{3}{16}$	$\frac{1}{8}$	$\frac{3}{16}$	$\frac{1}{8}$
Plasma torch-cut: ^G										
$\frac{3}{16}$ to 2, excl	$\frac{1}{2}$	0	$\frac{1}{2}$	0	$\frac{1}{2}$	0	$\frac{1}{2}$	0	$\frac{1}{2}$	0
2 to $2\frac{3}{4}$, incl	$\frac{5}{8}$	0	$\frac{5}{8}$	0	$\frac{5}{8}$	0	$\frac{5}{8}$	0	$\frac{5}{8}$	0
Millimetres										
Sheared: ^D										
4.8 to 7.9, excl	4.8	3.2	6.4	3.2	9.5	3.2	12.7	3.2	...	...
7.9 to 12.7, excl	6.4	3.2	9.5	3.2	9.5	3.2	12.7	3.2	15.9	3.2
12.7 to 19.1, excl	9.5	3.2	9.5	3.2	12.7	3.2	15.9	3.2	19.1	3.2
19.1 to 25.4, excl	12.7	3.2	12.7	3.2	15.8	3.2	19.1	3.2	22.2	3.2
25.4 to 31.8, incl	15.9	3.2	15.9	3.2	19.1	3.2	22.2	3.2	25.4	3.2
Abrasive-cut: ^{E,F}										
4.8 to 31.8, incl	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2
Over 31.8 to 69.8, incl	4.8	3.2	4.8	3.2	4.8	3.2	4.8	3.2	4.8	3.2
Plasma torch-cut: ^G										
4.8 to 50.8, excl	12.7	0	12.7	0	12.7	0	12.7	0	12.7	0
50.8 to 69.8, incl	15.9	0	15.9	0	15.9	0	15.9	0	15.9	0

^A Permissible variations in width for powder- or inert arc-cut plate shall be as agreed upon between the manufacturer and the purchaser.

^B Permissible variations in machined, powder-, or inert arc-cut circular plate shall be as agreed upon between the manufacturer and the purchaser.

^C Permissible variations in plasma torch-cut sketch plates shall be as agreed upon between the manufacturer and the purchaser.

^D The minimum sheared width is 24 in. (610 mm).

^E The minimum abrasive-cut width is 2 in. (50.8 mm) and increases to 4 in. (101.6 mm) for thicker plates.

^F These tolerances are applicable to lengths of 240 in. (6100 mm), max. For lengths over 240 in., an additional $\frac{1}{16}$ in. (1.6 mm) is permitted, both plus and minus.

^G The tolerance spread shown for plasma torch cutting may be obtained all on the minus side, or divided between the plus and minus side if so specified by the purchaser.



TABLE A3.5 Permissible Variations in Diameter for Circular Plates

Sheared Plate					
Specified Diameter, in. (mm)	Permissible Variations Over Specified Diameter for Thickness Given, in. (mm) ^A				
	To ⅜ (9.5), incl				
	¼ (6.4)				
	⅝ (7.9)				
	⅞ (9.5)				
108 to 140 (2740 to 3580), incl	⅞ (11.1)				
Plasma Torch-Cut Plate ^B					
Permissible Variations in Specified Diameter for Thickness Given, in. (mm) ^C					
Specified Diameter, in. (mm)	Thickness max, in. (mm)	⅜ to 2 (4.8 to 50.8), excl		2 to 2⅝ (50.8 to 69.8), incl	
		Plus	Minus	Plus	Minus
19 to 20 (483 to 508), excl	2⅝ (69.8)	½ (12.7)	0	⅝ (15.9)	0
20 to 22 (508 to 559), excl	2⅝ (69.8)	½ (12.7)	0	⅝ (15.9)	0
22 to 24 (559 to 610), excl	2½ (63.5)	½ (12.7)	0	⅝ (15.9)	0
24 to 28 (610 to 711), excl	2¼ (57.3)	½ (12.7)	0	⅝ (15.9)	0
28 to 32 (711 to 812), excl	2 (50.8)	½ (12.7)	0	⅝ (15.9)	0
32 to 34 (812 to 864), excl	1¾ (44.5)	½ (12.7)	0	...	...
34 to 38 (864 to 965), excl	1½ (38.1)	½ (12.7)	0	...	...
38 to 40 (965 to 1020), excl	1¼ (31.8)	½ (12.7)	0	...	...
40 to 140 (1020 to 3560), incl	2⅝ (69.8)	½ (12.7)	0	⅝ (15.9)	0

^A No permissible variations under.^B Permissible variations in plasma torch-cut sketch plates shall be as agreed upon between the manufacturer and the purchaser.^C The tolerance spread shown may also be obtained all on the minus side or divided between the plus and minus sides if so specified by the purchaser.

TABLE A3.6 Permissible Variations in Width of Sheet and Strip

Specified Thickness, in. (mm)	Specified Width, in. (mm)	Permissible Variations in Specified Width, in. (m)	
		Plus	Minus
	Sheet		
Up to 0.250 (6.35)	All	0.125 (3.18)	0
	Strip		
Under 0.075 (1.9)	Up to 12 (305), incl	0.007 (0.18)	0.007 (0.18)
	Over 12 to 48 (305 to 1219), incl	0.062 (1.6)	0
0.075 to 0.100 (1.9 to 2.5), incl	Up to 12 (305), incl	0.009 (0.23)	0.009 (0.23)
	Over 12 to 48 (305 to 1219), incl	0.062 (1.6)	0
Over 0.100 to 0.125 (2.5 to 3.2), incl	Up to 12 (305), incl	0.012 (0.30)	0.012 (0.30)
	Over 12 to 48 (305 to 1219), incl	0.062 (1.6)	0
Over 0.125 to 0.160 (3.2 to 4.1), incl	Up to 12 (305), incl	0.016 (0.41)	0.016 (0.41)
	Over 12 to 48 (305 to 1219), incl	0.062 (1.6)	0
Over 0.160 to 0.187 (4.1 to 4.7), incl	Up to 12 (305), incl	0.020 (0.51)	0.020 (0.51)
	Over 12 to 48 (305 to 1219), incl	0.062 (1.6)	0
Over 0.187 to 0.250 (4.7 to 6.4), incl	Up to 12 (305), incl	0.062 (1.6)	0.062 (1.6)
	Over 12 to 48 (305 to 1219), incl	0.062 (1.6)	0.062 (1.6)

TABLE A3.7 Permissible Variations in Length^A of Sheared, Plasma Torch-Cut,^B and Abrasive-Cut Rectangular Plate^C

Specified Thickness	Permissible Variation in Length for Lengths Given, in. (mm)															
	Up to 60 (1520), incl		Over 60 to 96 (1520 to 2440), incl		Over 96 to 120 (2440 to 3050), incl		Over 120 to 240 (3050 to 6096), incl		Over 240 to 360 (6096 to 9144), incl		Over 360 to 450 (9144 to 11 430), incl		Over 450 to 540 (11 430 to 13 716), incl		Over 540 (13 716)	
	Plus	Minus	Plus	Minus	Plus	Minus	Plus	Minus	Plus	Minus	Plus	Minus	Plus	Minus	Plus	Minus
Inches																
Sheared: ^D																
3/16 to 5/16, excl	3/16	1/8	1/4	1/8	3/8	1/8	1/2	1/8	5/8	1/8	3/4	1/8	7/8	1/8	...	...
5/16 to 1/2, excl	3/8	1/8	1/2	1/8	1/2	1/8	1/2	1/8	5/8	1/8	3/4	1/8	7/8	1/8	1	1/8
1/2 to 3/4, excl	1/2	1/8	1/2	1/8	5/8	1/8	5/8	1/8	3/4	1/8	7/8	1/8	1 1/8	1/8	1 3/8	1/8
3/4 to 1, excl	5/8	1/8	5/8	1/8	5/8	1/8	3/4	1/8	7/8	1/8	1 1/8	1/8	1 3/8	1/8	1 5/8	1/8
1 to 1 1/4, incl	3/4	1/8	3/4	1/8	3/4	1/8	7/8	1/8	1 1/8	1/8	1 3/8	1/8	1 5/8	1/8	...	...
Abrasive-cut: ^E																
3/16 to 1 1/4, incl	1/8	1/8	1/8	1/8	1/8	1/8	1/8	1/8	1/8	1/8	1/8	1/8	...	...	...	...
Over 1 1/4 to 2 3/4, incl	3/16	1/8	3/16	1/8	3/16	1/8	3/16	1/8	3/16	1/8	3/16	1/8	...	...	...	...
Plasma torch-cut: ^F																
3/16 to 2, excl	1/2	0	1/2	0	1/2	0	1/2	0	1/2	0	1/2	0	1/2	0	1/2	0
2 to 2 3/4	5/8	0	5/8	0	5/8	0	5/8	0	5/8	0	5/8	0	5/8	0	5/8	0
Millimetres																
Sheared: ^D																
4.8 to 7.94, excl	4.8	3.2	6.4	3.2	9.5	3.2	12.7	3.2	15.9	3.2	19.0	3.2	22.2	3.2	...	...
7.94 to 12.7, excl	9.5	3.2	12.7	3.2	12.7	3.2	12.7	3.2	15.9	3.2	19.0	3.2	22.2	3.2	25.4	3.2
12.7 to 19.0, excl	12.7	3.2	12.7	3.2	15.9	3.2	15.9	3.2	19.0	3.2	22.2	3.2	28.6	3.2	34.9	3.2
19.0 to 25.4, excl	15.9	3.2	15.9	3.2	15.9	3.2	19.0	3.2	22.2	3.2	28.6	3.2	34.9	3.2	41.2	3.2
25.4 to 31.8, incl	19.0	3.2	19.0	3.2	19.0	3.2	22.2	3.2	28.6	3.2	34.9	3.2	41.2	3.2	...	...
Abrasive-cut: ^E																
4.8 to 31.8, incl	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	3.2	...	...	...	...
Over 31.8 to 69.9, incl	4.8	3.2	4.8	3.2	4.8	3.2	4.8	3.2	4.8	3.2	4.8	3.2	...	...	...	...
Plasma torch-cut: ^F																
4.8 to 50.8, excl	12.7	0	12.7	0	12.7	0	12.7	0	12.7	0	12.7	0	12.7	0	12.7	0
50.8 to 69.9, incl	15.9	0	15.9	0	15.9	0	15.9	0	15.9	0	15.9	0	15.9	0	15.9	0

^A Permissible variations in length for powder- or inert arc-cut plate shall be agreed upon between the manufacturer and the purchaser.

^B The tolerance spread shown for plasma torch cutting may be obtained all on the minus side, or divided between the plus and minus sides if so specified by the purchaser.

^C Permissible variations in machined, powder- or inert arc-cut circular plate shall be as agreed upon between the manufacturer and the purchaser.

^D The minimum sheared length is 24 in. (610 mm).

^E Abrasive cut applicable to a maximum length of 144 to 400 in. (3658 to 10 160 mm), depending on the thickness and width ordered.

^F The tolerance spread shown for plasma torch-cut sketch plates shall be as agreed upon between the manufacturer and the purchaser.

A4. REQUIREMENTS FOR THE INTRODUCTION OF NEW MATERIALS

A4.1 New materials may be proposed for inclusion in specifications referencing this specification of general requirements subject to the following conditions:

A4.1.1 Application for the addition of a new grade to a specification shall be made to the chair of B02.07 or presented to the B02.07 subcommittee.

A4.1.2 The application shall be accompanied by a statement from at least one user indicating that there is a need for the new grade to be included in the applicable specification.

A4.1.3 The application shall be accompanied by test data as required by the applicable product specification. Test data from a minimum of three test lots, as defined by the specification, each from a different heat, shall be furnished.

A4.1.3.1 Exceptions to the requirements cited in A4.1.3 may be requested by the applicant and shall require the review and approval of the subcommittee. The application shall include the rationale for the reduction in the test data to be furnished. The reduced amount data to be furnished should be sufficient, as determined by the subcommittee, to provide reasonable assurance that the proposed minimum specification requirements are likely to be satisfied by subsequent production. At a minimum, test data from one heat and two heat treat lots, shall be furnished.

A4.1.4 The application shall provide recommendations for all requirements appearing in the applicable specification.

A4.1.5 The application shall state whether the new grade is covered by patent.

A5. REQUIREMENTS FOR THE INTRODUCTION OF MATERIALS FROM OTHER B02.07 SPECIFICATIONS

A5.1 Wrought materials that are already covered by another B02.07 specification may be proposed for inclusion in specifications referencing this specification of general requirements subject to the following conditions:

A5.1.1 Application for the addition of a grade that is already covered in another B02.07 specification shall be made to the chair of B02.07 or presented to the B02.07 subcommittee.

A5.1.2 The chemical requirements, the specified mechanical properties, and the heat treatment requirements of the grade

being added shall be the same as those for the grade in the B02.07 specification in which the grade is presently covered.

A5.1.3 The application shall provide recommendations for all requirements appearing in the applicable product specification.

A5.1.4 The application shall state whether the grade is covered by patent.

SUMMARY OF CHANGES

Committee B02 has identified the location of selected changes to this standard since the last issue (B906 – 19) that may impact the use of this standard. (Approved July 15, 2022.)

(1) Added reference to Terminology B899 and updated Section 3.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/