

# Stainless steel tubes — Dimensions, tolerances and conventional masses per unit length

The European Standard EN ISO 1127:1996 has the status of a  
British Standard

ICS 23.040.10

# Committees responsible for this British Standard

The preparation of this British Standard was entrusted to Technical Committee ISE/8, Steel pipes, upon which the following bodies were represented:

Adhesive Tape Manufacturers' Association  
 British Compressed Air Society  
 British Iron and Steel Producers' Association  
 British Malleable Tubes Fittings Association  
 British Stainless Steel Association  
 British Valve and Actuator Manufacturers' Association  
 British Welded Steel Tube Association  
 Engineering Equipment and Materials Users' Association  
 Food and Drink Federation  
 Institution of Civil Engineers  
 Institution of Gas Engineers  
 Institution of Water and Environmental Management  
 Large Diameter Steel Tube Association  
 Mechanical Handling Engineers' Association  
 National Association of Plumbing, Heating and Mechanical Services Contractors  
 Seamless Steel Tube Association  
 Steel Construction Institute  
 Steel Tube Fittings Manufacturers' Technical Association  
 Society of Motor Manufacturers and Traders Ltd.  
 Water Companies Association  
 Water Services Association of England and Wales  
 Co-opted member

This British Standard, having been prepared under the direction of the Engineering Sector Board, was published under the authority of the Standards Board and comes into effect on 15 January 1997

© BSI 11-1998

The following BSI references relate to the work on this standard:  
 Committee reference ISE/8  
 Draft announced in *BSI News* March 1994

## Amendments issued since publication

Amd. No.	Date	Comments

ISBN 0 580 26142 5

---

# Contents

	Page
Committees responsible	Inside front cover
National foreword	ii
<hr/>	
Foreword	2
1 Scope	3
2 Normative references	3
3 Dimensions	3
4 Tolerances	3
5 Conventional masses per unit length	3
<hr/>	
Annex A (informative) Bibliography	8
<hr/>	
Table 1 — Tolerances on outside diameter	3
Table 2 — Tolerances on thickness	3
Table 3 — Conventional masses for austenitic stainless steel tubes	4
Table 4 — Conventional masses for ferritic and martensitic stainless steel tubes	6
<hr/>	

## National foreword

This British Standard has been prepared by Technical Committee ISE/8 *Stainless steel tubes — Dimensions, tolerances and conventional masses per unit length*, and is the English language version of EN ISO 1127:1996, published by the European Committee for Standardization (CEN). It is identical with ISO 1127:1992, prepared by ISO/TC 5, Ferrous metal pipes and metallic fittings, of the International Organization for Standardization (ISO) with the active participation of the UK.

It supersedes certain specifications in BS 3600:1976 which are deleted by amendment.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

### Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, the EN title page, pages 2 to 8 and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

---

ICS 23.040.10

Descriptors: Piping, stainless steels, austenitic steels, ferritic steels, martensitic steels, steel tubes, dimensions, dimensional tolerances, linear density

English version

## Stainless steel tubes — Dimensions, tolerances and conventional masses per unit length

(ISO 1127:1992)

Tubes en acier inoxydable — Dimensions, tolérances et masses linéiques conventionnelles (ISO 1127:1992)

Nichtrostende Stahlrohre — Masse, Grenzabmasse und längenbezogene Masse (ISO 1127:1992)

This European Standard was approved by CEN on 1996-02-16. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

# CEN

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

## **Foreword**

The text of the International Standard from Technical Committee ISO/TC 5, Ferrous metal pipes and metallic fittings, of the International Organization for Standardization (ISO) has been taken over as an European Standard by Technical Committee ECISS/TC 29, Steel tubes and fittings for steel tubes, the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 1996, and conflicting standards shall be withdrawn at the latest by October 1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

## 1 Scope

This International Standard specifies the diameters, thicknesses, tolerances and conventional masses per unit length of stainless steel tubes.

## 2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards. ISO 5252:1991, *Steel tubes — Tolerance systems*.

## 3 Dimensions

The outside diameters and thicknesses of the tubes specified in this International Standard have been selected from ISO 4200. If thicknesses greater than 14,2 mm are needed, they should be chosen from ISO 4200.

## 4 Tolerances

The tolerances permitted on the outside diameter and thickness of the tubes result from the method of manufacture, the steel types and the heat treatment. The tolerances shall be selected from the values given in Table 1 and Table 2.

### 4.1 Tolerances on outside diameter

See Table 1.

**Table 1 — Tolerances on outside diameter**

Tolerance class	Tolerance on outside diameter
D <sub>1</sub>	± 1,5 % with ± 0,75 mm min.
D <sub>2</sub>	± 1 % with ± 0,5 mm min.
D <sub>3</sub>	± 0,75 % with ± 0,3 mm min.
D <sub>4</sub>	± 0,5 % with ± 0,1 mm min.

The tolerances on outside diameter include ovality.

### 4.2 Tolerances on thickness

See Table 2.

**Table 2 — Tolerances on thickness**

Tolerance class	Tolerance on thickness
T <sub>1</sub>	± 15 % with ± 0,6 mm min.
T <sub>2</sub>	± 12,5 % with ± 0,4 mm min.
T <sub>3</sub>	± 10 % with ± 0,2 mm min.
T <sub>4</sub>	± 7,5 % with ± 0,15 mm min.
T <sub>5</sub>	± 5 % with ± 0,1 mm min.

The tolerances on thickness include eccentricity.

### 4.3 Other tolerances

For tolerances on dimensions other than outside diameter and thickness, reference shall be made to ISO 5252.

## 5 Conventional masses per unit length

The conventional masses per unit length given in Table 3 for austenitic stainless steel tubes are the masses given in ISO 4200 multiplied by a factor of 1,015. This factor assumes an average density for these tubes of 7,97 kg/dm<sup>3</sup>.

The conventional masses per unit length given in Table 4 for ferritic and martensitic stainless steel tubes are the masses given in ISO 4200 multiplied by a factor of 0,985. This factor assumes an average density for these tubes of 7,73 kg/dm<sup>3</sup>.

Table 3 — Conventional masses for austenitic stainless steel tubes

Outside diameter mm			Thickness, mm																				
			1,0	1,2	1,6	2,0	2,3	2,6	2,9	3,2	3,6	4,0	4,5	5,0	5,6	6,3	7,1	8,0	8,8	10,0	11,0	12,5	14,2
Series			Conventional mass per unit length, kg/m																				
1	2	3																					
	6		0,125	0,144																			
	8		0,176	0,204																			
	10		0,225	0,264																			
10,2			0,230	0,270	0,344	0,410																	
	12		0,275		0,416	0,500																	
	12,7		0,293	0,345	0,445	0,536	0,599	0,658	0,711	0,761													
13,5			0,313	0,369	0,477	0,576	0,645		0,769														
		14	0,326		0,496	0,601																	
	16		0,376	0,445	0,577	0,701																	
17,2			0,406		0,625	0,761	0,858			1,12													
		18	0,425		0,657	0,801																	
	19		0,451	0,535	0,697	0,851																	
	20		0,476	0,564	0,737	0,901																	
21,3			0,509		0,789	0,966		1,22		1,45		1,74											
		22	0,526			1,00																	
	25		0,601	0,715	0,937	1,15		1,46															
		25,4		0,727	0,953	1,17		1,48															
26,9			0,649		1,01	1,25		1,58	1,75	1,90		2,29											
		30			1,14	1,40																	
	31,8			0,920	1,21	1,49		1,90		2,29		2,78											
	32			0,925		1,50																	
33,7			0,818	0,976	1,29	1,58	1,81	2,02		2,45		3,29											
		35		1,02		1,65																	
	38			1,11	1,46	1,81		2,30		2,79													
	40			1,17	1,54			2,44															
42,4					1,63	2,02		2,59		3,14	3,49			4,68									
		44,5				2,13		2,73	3,02														

Table 3 — Conventional masses for austenitic stainless steel tubes

Outside diameter mm			Thickness, mm																					
			1,0	1,2	1,6	2,0	2,3	2,6	2,9	3,2	3,6	4,0	4,5	5,0	5,6	6,3	7,1	8,0	8,8	10,0	11,0	12,5	14,2	
Series			Conventional mass per unit length, kg/m																					
1	2	3																						
48,3			1,25	1,49	1,87	2,31		2,97		3,61	4,03			5,42										
	51				1,98	2,46		3,15		3,83														
		54			2,10	2,60		3,35																
	57				2,22	2,75			3,93															
60,3					2,35	2,92	3,34	3,76	4,17	4,58	5,11	5,63		7,66										
	63,5				2,48	3,08		3,96		4,83														
	70				2,74	3,40			4,87															
76,1					2,98	3,70	4,25	4,78	5,32		6,54	7,22		8,90					12,3					
		82,5				4,03				6,35														
88,9					3,49	4,35	4,98	5,61	6,24	6,86	7,68	8,51		11,7					16,2					
	101,6				4,98				7,17			9,77		13,5					18,8					
114,3					4,52	5,62		7,27	8,09		9,98		12,4			17,1			23,2					
139,7					5,53	6,89		8,92		11,0		13,6		16,8		21,0	23,5			32,5				
168,3					6,68	8,32		10,8		13,2		16,4	18,5	20,4		28,6				43,3				
219,1						10,9		14,1		17,3	19,4	21,5				33,6		42,2				64,7		
273						13,6		17,6		21,6	24,3	26,9				42,0				65,9		81,5	92,0	
323,9								20,9		25,7		32,1	35,9	39,9		56,3				78,6		97,4		
355,6								22,9		28,2		35,2		43,8						86,5	94,9	108		
406,4								26,3		32,3		40,3		50,2						99,3		123		
457										36,3		45,4		56,5						112		139	157	
508										40,4	45,5			62,9	70,4						137	155	176	
610										48,6		60,7			84,8	95,2						187	212	
711																	125							
813																		161						
914																			199					
1016																				252				

Table 4 — Conventional masses for ferritic and martensitic stainless steel tubes

Outside diameter mm			Thickness, mm																				
			1,0	1,2	1,6	2,0	2,3	2,6	2,9	3,2	3,6	4,0	4,5	5,0	5,6	6,3	7,1	8,0	8,8	10,0	11,0	12,5	14,2
Series			Conventional mass per unit length, kg/m																				
1	2	3																					
	6		0,121	0,140																			
	8		0,170	0,198																			
	10		0,219	0,256																			
	10,2		0,224	0,262	0,334	0,398																	
	12		0,267		0,404	0,486																	
	12,7		0,285	0,335	0,431	0,520	0,581	0,638	0,690	0,739													
	13,5		0,303	0,359	0,463	0,558	0,625		0,747														
		14	0,316		0,482	0,583																	
	16		0,364	0,431	0,559	0,681																	
	17,2		0,394		0,607	0,739	0,832			1,08													
		18	0,413		0,637	0,777																	
	19		0,437	0,519	0,677	0,825																	
	20		0,462	0,548	0,715	0,875																	
	21,3		0,493		0,765	0,938		1,18		1,41		1,68											
		22	0,510			0,971																	
	25		0,583	0,693	0,909	1,11		1,42															
		25,4		0,705	0,925	1,13		1,44															
26,9			0,629		0,983	1,21		1,54	1,69	1,84		2,23											
		30			1,10	1,36																	
	31,8			0,892	1,17	1,45		1,84		2,23		2,70											
	32			0,897		1,46																	
33,7			0,794	0,948	1,25	1,54	1,75	1,96		2,37		3,19											
		35		0,985		1,61																	
	38			1,07	1,42	1,75		2,24		2,71													
	40			1,13	1,50			2,36															
42,4					1,59	1,96		2,51		3,04	3,39		4,54										

Table 4 — Conventional masses for ferritic and martensitic stainless steel tubes

Outside diameter mm			Thickness, mm																				
			1,0	1,2	1,6	2,0	2,3	2,6	2,9	3,2	3,6	4,0	4,5	5,0	5,6	6,3	7,1	8,0	8,8	10,0	11,0	12,5	14,2
Series			Conventional mass per unit length, kg/m																				
1	2	3																					
		44,5				2,07		2,65	2,94														
48,3					1,81	2,25		2,89		3,51	3,91			5,26									
	51		1,21	1,45	1,92	2,38		3,05		3,71													
		54			2,04	2,52		3,25															
	57				2,16	2,67			3,81														
60,3					2,29	2,84	3,24	3,64	4,05	4,44	4,95	5,47			7,44								
	63,5				2,40	2,98		3,84		4,69													
	70				2,66	3,30			4,73														
76,1					2,90	3,60	4,13	4,64	5,16		6,34	7,00		8,64					11,9				
		82,5				3,91			6,17														
88,9					3,39	4,23	4,84	5,45	6,06	6,66	7,46	8,25			11,3				15,8				
	101,6				4,84				6,95		9,49				13,1				18,2				
114,3					4,38	5,46		7,05	7,85		9,68		12,0			16,5			22,6				
139,7					5,37	6,69		8,66		10,6		13,2		16,4		20,4	22,9				31,5		
168,3					6,48	8,08		10,4		12,8		16,0	17,9	19,8			27,8				42,1		
219,1					10,5			13,7		16,7	18,8	20,9				32,6		41,0				62,7	
273					13,2			17,0		21,0	23,5	26,1				40,8				63,9		79,1	89,2
323,9								20,3		24,9		31,1	34,9	38,7			54,7				76,2		94,6
355,6								22,3		27,4		34,2		42,6						83,9	92,1	104	
406,4								25,5		31,3		39,1		48,8						96,3		119	
457										35,3		44,0		54,9						108		135	153
508										39,2	44,1			61,1	68,4						133	151	170
610										47,2		58,9			82,2	92,4					181	206	
711																	121						
813																	157						
914																		193					
1 016																				244			

## **Annex A (informative)**

### **Bibliography**

[1] ISO 4200:1991, *Plain end steel tubes, welded and seamless — General tables of dimensions and masses per unit length.*



---

---

# BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

## Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

## Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

## Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

## Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.